



BSI Standards Publication

**International comparison of
measurements of the magnetic
moment using vibrating sample
magnetometers (VSM) and
superconducting quantum
interference device (SQUID)
magnetometers**

National foreword

This Published Document is the UK implementation of IEC/TR 62797:2013.

The UK participation in its preparation was entrusted to Technical Committee ISE/108, Magnetic Alloys and Steels.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013.
Published by BSI Standards Limited 2013

ISBN 978 0 580 79772 9
ICS 29.030

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 August 2013.

Amendments/corrigenda issued since publication

Date	Text affected
-------------	----------------------



TECHNICAL REPORT



International comparison of measurements of the magnetic moment using vibrating sample magnetometers (VSM) and superconducting quantum interference device (SQUID) magnetometers

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE



ICS 29.030

ISBN 978-2-8322-1018-5

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Overview.....	7
3 Samples.....	8
3.1 Hard ferrites.....	8
3.2 Magnetic tapes.....	8
4 Measuring quantities and measuring conditions.....	8
4.1 General.....	8
4.2 Hard ferrite spheres.....	8
4.3 Magnetic tape samples.....	9
4.4 Role of the measuring temperature.....	9
5 Analysis of the measured quantities.....	10
Annex A (informative) International comparison of measurements of the magnetic moment using vibrating sample magnetometers and SQUID magnetometers.....	15
Annex B (informative) Participants.....	30
Bibliography.....	31
Figure 1 – Isotropic and anisotropic ferrites: standard deviations.....	12
Figure 2 – Magnetic tape samples: standard deviations.....	12
Figure 3 – Isotropic and anisotropic ferrites: weighted uncertainties.....	13
Figure 4 – Magnetic tape samples: weighted uncertainties.....	13
Figure 5 – Normalized best values $y_i / \langle y \rangle$ of the coercive field strength H_{CJ} and maximum energy product $(BH)_{max}$	14
Figure A.1 – Dispersion of the J_{800k} values measured by the participating laboratories on the isotropic ferrite sample HF-Iso1.....	16
Figure A.2 – Dispersion of the J_r values measured by the participating laboratories on the isotropic ferrite sample HF-Iso1.....	17
Figure A.3 – Dispersion of the H_{CJ} values measured by the participating laboratories on the isotropic ferrite sample HF-Iso1.....	18
Figure A.4 – Dispersion of the H_{CB} values measured by the participating laboratories on the isotropic ferrite sample HF-Iso1.....	19
Figure A.5 – Dispersion of the $(BH)_{max}$ values measured by the participating laboratories on the isotropic ferrite sample HF-Iso1.....	20
Figure A.6 – Dispersion of the J_{800k} values measured by the participating laboratories on the anisotropic ferrite sample HF-Aniso1.....	21
Figure A.7 – Dispersion of the J_r values measured by the participating laboratories on the anisotropic ferrite sample HF-Aniso1.....	22
Figure A.8 – Dispersion of the H_{CJ} values measured by the participating laboratories on the anisotropic ferrite sample HF-Aniso1.....	23
Figure A.9 – Dispersion of the H_{CB} values measured by the participating laboratories on the anisotropic ferrite sample HF-Aniso1.....	24
Figure A.10 – Dispersion of the $(BH)_{max}$ values measured by the participating laboratories on the anisotropic ferrite sample HF-Aniso1.....	25
Figure A.11 – Dispersion of the m_{400k} values measured by the participating laboratories on the magnetic tape sample A1.....	26

Figure A.12 – Dispersion of the m_r values measured by the participating laboratories on the magnetic tape sample A1	27
Figure A.13 – Dispersion of the $S = m_r/m_{400k}$ values measured by the participating laboratories on the magnetic tape sample A1	28
Figure A.14 – Dispersion of the H_{CJ} values measured by the participating laboratories on the magnetic tape sample A1	29
Table A.1 – Magnetic polarization value J_{800k} at $H_a = H_{peak} = 800$ kA/m measured by the participating laboratories on the isotropic hard ferrite HF-Iso1	15
Table A.2 – Remanent magnetic polarization J_r measured by the participating laboratories on the isotropic hard ferrite HF-Iso1	17
Table A.3 – Coercive field H_{CJ} measured by the participating laboratories on the isotropic hard ferrite HF-Iso1	18
Table A.4 – Coercive field H_{CB} measured by the participating laboratories on the isotropic hard ferrite HF-Iso1	19
Table A.5 – Maximum energy product $(BH)_{max}$ measured by the participating laboratories on the isotropic hard ferrite HF- Iso1	20
Table A.6 – Magnetic polarization value J_{800k} at $H_a = H_{peak} = 800$ kA/m measured by the participating laboratories on the anisotropic hard ferrite HF-Aniso1	21
Table A.7 – Remanent magnetic polarization J_r measured by the participating laboratories on the anisotropic hard ferrite HF-Aniso1	22
Table A.8 – Coercive field H_{CJ} measured by the participating laboratories on the anisotropic hard ferrite HF-Aniso1	23
Table A.9 – Coercive field H_{CB} measured by the participating laboratories on the anisotropic hard ferrite HF-Aniso1	24
Table A.10 – Maximum energy product $(BH)_{max}$ measured by the participating laboratories on the anisotropic hard ferrite HF- Aniso1	25
Table A.11 – Magnetic moment m_{400k} measured at $H_a = H_{peak} = 400$ kA/m by the participating laboratories on the magnetic tape sample 1A	26
Table A.12 – Remanent magnetic moment m_r measured by the participating laboratories on the magnetic tape sample 1A	27
Table A.13 – Squareness ratio $S = m_r/m_{400k}$ measured by the participating laboratories on the magnetic tape sample 1A	28
Table A.14 – Coercive field H_{CJ} measured by the participating laboratories on the magnetic tape sample 1A	29

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**INTERNATIONAL COMPARISON OF MEASUREMENTS OF
THE MAGNETIC MOMENT USING VIBRATING SAMPLE
MAGNETOMETERS (VSM) AND SUPERCONDUCTING
QUANTUM INTERFERENCE DEVICE (SQUID) MAGNETOMETERS**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC 62797, which is a technical report, has been prepared by IEC technical committee 68: Magnetic alloys and steels.

The text of this technical report is based on the following documents:

Enquiry draft	Report on voting
68/448/DTR	68/454/RVC

Full information on the voting for the approval of this technical report can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A bilingual version of this publication may be issued at a later date.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

Following a proposal made at the meeting of IEC TC 68 Working Group 2 (Magnetic alloys and steels – Measuring methods) in Braunschweig (PTB, 13-14 November 2006), an intercomparison exercise was started regarding the measurement of the magnetic moment by means of the vibrating sample magnetometer (VSM) method. The VSM finds widespread use in industrial and research laboratories, because of its sensitivity, ruggedness, and relative simplicity of use [1]¹. It is not an absolute method and requires calibration by means of a reference sample. This is typically represented by a very pure Ni sphere, calibrated by means of an independent method [2]. The VSM is generally applied for the characterization of hard magnetic materials, but, depending on the specific sensitivity of the apparatus, can also be used to test paramagnetic and diamagnetic materials. Its application to magnetically soft materials is generally restricted to the determination of the saturation magnetization. In fact, being an open circuit method, the VSM is not suited to the measurement of the magnetization curve of soft magnetic materials.

The basic aim of this comparison is to verify the degree of reproducibility of the method, a prerequisite for the prospective development of a related IEC measuring standard. The existing ASTM Standard A894/894M-00 [3] is devoted to the determination of the saturation magnetization of nonmetallic magnetic materials. Ten different research laboratories, listed in Annex B, agreed to participate in the comparison exercise. Each laboratory was assumed to have appropriate traceability of measurements and was required to determine the measurement uncertainty according to the ISO/IEC Guide to the expression of uncertainty in measurement [4]. Two laboratories used superconducting quantum interference device (SQUID) magnetometers.

The comparison was coordinated by INRIM (Istituto Nazionale di Ricerca Metrologica, Torino, Italy) and the Hannam University (Taejon, Korea). A summarizing paper on these experiments was presented at the International Workshop on One- and Two-Dimensional Measurement and Testing (Vienna, September 2012) and is to be published on the Int. J. Appl. Electromagnetics and Mechanics [8].

¹ Numbers in square brackets refer to the Bibliography.

INTERNATIONAL COMPARISON OF MEASUREMENTS OF THE MAGNETIC MOMENT USING VIBRATING SAMPLE MAGNETOMETERS (VSM) AND SUPERCONDUCTING QUANTUM INTERFERENCE DEVICE (SQUID) MAGNETOMETERS

1 Scope

This Technical Report provides the results of an international comparison of measurements of the magnetic moment, using vibrating sample magnetometers (VSM) and superconducting quantum interference device (SQUID) magnetometers.

The basic object of this comparison is to verify the degree of reproducibility of the method employed as a prerequisite for the prospective development of a related IEC measuring standard.

2 Overview

In this report an intercomparison exercise on the measurement of the magnetic moment by means of the vibrating sample magnetometer (VSM) and superconducting quantum interference device (SQUID) magnetometer is presented. The VSM finds widespread use in industrial and research laboratories, because of its sensitivity, ruggedness, and relative simplicity of use. The basic aim of this comparison was to verify the degree of reproducibility of the VSM method, as a prerequisite for the prospective development of a related IEC measuring standard. At present time, the VSM method is invoked in the ASTM Standard A984, which is devoted, however, exclusively to the determination of the saturation magnetization of nonmetallic magnetic materials. An exercise was carried out by ten different laboratories regarding the measurement of the hysteresis loop parameters in hard ferrites and the magnetic moment in tape samples by means of the VSM (SI units). Each laboratory was assumed to have appropriate traceability of measurements and was required to determine the measurement uncertainty according to the ISO/IEC Guide to the expression of uncertainty in measurement. The comparison was coordinated by INRIM. The results were analyzed according to standard rules (e.g. ISO and EURAMET guidelines).

The following relative standard deviations of the laboratories best estimates around the unweighted mean were found:

- a) Anisotropic hard ferrites: coercive field $H_{cJ} \sim 1,0 \%$; coercive field $H_{cB} \sim 0,9 \%$; polarization at applied field $H_a \sim 800 \text{ kA/m}$ $J_{800k} \sim 0,80 \%$; remanent polarization $J_r \sim 1,8 \%$; maximum energy product $(BH)_{\max} \sim 1,2 \%$.
- b) Isotropic hard ferrites: coercive field $H_{cJ} \sim 1,0 \%$; coercive field $H_{cB} \sim 3,5 \%$; polarization at applied field $H_a = 800 \text{ kA/m}$ $J_{800k} \sim 1,2 \%$; remanent polarization $J_r \sim 3,2 \%$; maximum energy product $(BH)_{\max} \sim 6,2 \%$.
- c) Magnetic tape samples: magnetic moment at $H_a = 400 \text{ kA/m}$ $m_{400k} \sim 1,8 \%$ - $2,8 \%$; remanent magnetic moment $m_r \sim 1,3 \%$ - $1,6 \%$; squareness $S \sim 2,0 \%$; coercive field $H_{cJ} \sim 1,1 \%$ - $2,2 \%$.