



BSI Standards Publication

Bitumen and bituminous binders — Determination of the fracture toughness temperature by a three point bending test on a notched specimen

National foreword

This Published Document is the UK implementation of CEN/TS 15963:2014. It supersedes DD CEN/TS 15963:2010, BS 2000-584:2010 which is withdrawn.

The UK participation in its preparation was entrusted by Technical Committee B/510, Road materials, to Subcommittee B/510/19, Bitumen and related products.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014.
Published by BSI Standards Limited 2014

ISBN 978 0 580 79758 3
ICS 91.100.50

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 30 June 2014.

Amendments/corrigenda issued since publication

Amd. No.	Date	Text affected
----------	------	---------------

TECHNICAL SPECIFICATION
 SPÉCIFICATION TECHNIQUE
 TECHNISCHE SPEZIFIKATION

CEN/TS 15963

April 2014

ICS 91.100.50

Supersedes CEN/TS 15963:2010

English Version

Bitumen and bituminous binders - Determination of the fracture toughness temperature by a three point bending test on a notched specimen

Bitumes et liants bitumineux - Détermination de la température de résistance à la fissuration par un essai de flexion 3 points sur un barreau entaillé

Bitumen und bitumenhaltige Bindemittel - Bestimmung der Bruchwiderstandstemperatur mittels eines Drei-Punkt-Biegeversuches an einem gekerbten Probekörper

This Technical Specification (CEN/TS) was approved by CEN on 16 December 2013 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
 COMITÉ EUROPÉEN DE NORMALISATION
 EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Principle	6
5 Apparatus	6
5.1 Testing apparatus	6
5.2 Test specimen	8
6 Preparation of test samples.....	9
6.1 Preparation of test samples.....	9
6.2 Preparation of moulds.....	9
6.3 Preparation of test specimen	11
7 Procedure to determine the Fracture Toughness temperature T_{FT}	12
7.1 Number of tests.....	12
7.2 Specimen conditioning	12
7.3 Loading rate and test temperature.....	12
7.4 Validity of the test results	12
7.5 Fracture Toughness temperature, T_{FT}	12
8 Calculation.....	12
8.1 Test sample	12
8.2 Results and temperature.....	13
8.3 Fracture Toughness temperature, T_{FT}	13
9 Expression of results	14
9.1 Fracture Toughness temperature, T_{FT}	14
9.2 Other properties.....	14
10 Precision.....	14
10.1 Repeatability.....	14
10.2 Reproducibility.....	14
11 Test report	15
Annex A (informative) Calculation of Critical Stress Intensity factor	16
A.1 General.....	16
A.2 Terms and definitions	16
A.3 Calculations.....	16
Bibliography	18

Foreword

This document (CEN/TS 15963:2014) has been prepared by Technical Committee CEN/TC 336 "Bituminous binders", the secretariat of which is held by AFNOR.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 15963:2010.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This Technical Specification specifies a method for the determination of the Fracture Toughness temperature, T_{FT} , of bituminous binders by means of a three point bending test on a notched binder sample.

WARNING — The use of this Technical Specification can involve hazardous materials, operations and equipment. This Technical Specification does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this Technical Specification to establish appropriate safety and health practices and to determine the applicability of regulatory limitations prior to use. For environmental reasons, it is recommended to limit the use of products, solvents and energy to minimum in order to reduce the emissions to air, water and soil.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 58, *Bitumen and bituminous binders - Sampling bituminous binders*

EN 12594, *Bitumen and bituminous binders - Preparation of test samples*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 maximum force

F
highest force measured during the bending test

Note 1 to entry: The test is done in the brittle state or close to that, so that the maximum force is considered as the onset of the crack propagation.

Note 2 to entry: Force is expressed in newtons (N).

3.2 displacement at maximum force

D
bending of the test beam from the beginning of the test (from the zero point) to the break point

Note 1 to entry: Displacement is expressed in millimetres (mm).

3.3 work

W
area under the force-displacement curve from the beginning of the test to the break of the sample, i.e. at the maximum force

Note 1 to entry: Work is expressed in newtons-metres (N·m) or in Joules (J).