



BSI Standards Publication

**Secondary cells and
batteries containing
alkaline or other non-acid
electrolytes — Experimental
procedure for the forced
internal short-circuit test
of IEC 62133:2012**

National foreword

This Published Document is the UK implementation of IEC/TR 62914:2014.

The UK participation in its preparation was entrusted by Technical Committee PEL/21, Secondary cells and batteries, to Subcommittee PEL/21/1, Secondary cells and batteries containing alkaline and other non-acidic electrolytes.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014.
Published by BSI Standards Limited 2014

ISBN 978 0 580 85992 2
ICS 29.220.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 30 September 2014.

Amendments/corrigenda issued since publication

Date	Text affected
-------------	----------------------



TECHNICAL REPORT



Secondary cells and batteries containing alkaline or other non-acid electrolytes – Experimental procedure for the forced internal short-circuit test of IEC 62133:2012

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE



ICS 29.220.30

ISBN 978-2-8322-1622-4

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Experimental procedure of the forced internal short-circuit test.....	6
3.1 Example of preparation of nickel particle.....	6
3.1.1 Material and tools	6
3.1.2 Example of a nickel particle preparation procedure.....	6
3.2 Positioning (or placement) of a nickel particle	7
3.3 Damaged separator precaution	8
3.4 Caution for rewind separator and electrode.....	8
3.5 Insulation film for preventing short circuit.....	8
3.6 Cautions on disassembling cell	8
3.7 Protective goods for safety	9
3.8 Cautions in case of fire during disassembling	9
3.9 Cautions for disassembling process and pressurizing electrode core	9
3.10 Recommended specifications of a pressurizing device	9
Bibliography.....	11
Figure 1 – Dimensions of a completed nickel particle.....	7
Figure 2 – Positioning of nickel particle when it cannot be placed in the specified area.....	8
Figure 3 – Cylindrical cell.....	8
Figure 4 – Distance / time ratio of several types of pressurizing devices	10
Table 1 – Recommended specifications of a pressurizing device	10

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**SECONDARY CELLS AND BATTERIES CONTAINING ALKALINE
OR OTHER NON-ACID ELECTROLYTES – EXPERIMENTAL
PROCEDURE FOR THE FORCED INTERNAL
SHORT-CIRCUIT TEST OF IEC 62133:2012**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC/TR 62914, which is a technical report, has been prepared by subcommittee 21A: Secondary cells and batteries containing alkaline or other non-acid electrolytes, of IEC technical committee 21: Secondary cells and batteries.

The text of this technical report is based on the following documents:

Enquiry draft	Report on voting
21A/537/DTR	21A/549/RVC

Full information on the voting for the approval of this technical report can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

The second edition of IEC 62133 was published on December, 2012. This technical report provides supplemental information to perform the forced internal short-circuit test of IEC 62133:2012.

SECONDARY CELLS AND BATTERIES CONTAINING ALKALINE OR OTHER NON-ACID ELECTROLYTES – EXPERIMENTAL PROCEDURE FOR THE FORCED INTERNAL SHORT-CIRCUIT TEST OF IEC 62133:2012

1 Scope

This Technical Report identifies experimental procedures for the forced internal short-circuit tests in terms of designation, dimensions, tests and requirements. It supplements 8.3.9 of IEC 62133:2012.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 62133:2012, *Secondary cells and batteries containing alkaline or other non-acid electrolytes – Safety requirements for portable sealed secondary cells, and for batteries made from them, for use in portable applications*

3 Experimental procedure of the forced internal short-circuit test

3.1 Example of preparation of nickel particle

3.1.1 Material and tools

The necessary material and tools required for this preparation are listed below.

- a) a nickel piece: Prepare nickel plate (soft temper; ISO 6208, NW2200 (Ni 99.0) or NW2201 (Ni 99.0 -LC) $0,10 \pm 0,01$ mm thick made into a piece $0,20^{+0,05}_{-0,03}$ mm wide and $2,00 \pm 0,30$ mm long by slit processing or using a punching press;
- b) a stereomicroscope;
- c) a cutter knife;
- d) glass slides (2 slides: 1 mm or thicker with square corners);
- e) a graph paper (1 mm square);
- f) a storage container for nickel particles.

3.1.2 Example of a nickel particle preparation procedure

The following steps are to be undertaken:

- a) place graph paper on the stage of the stereomicroscope and focus the microscope on the lines of the graph paper;
- b) while looking through the microscope, place the nickel piece parallel to a line of the graph paper. The nickel piece should be placed horizontally, with its 0,20 mm sides extending downward perpendicularly from and its 2,0 mm sides running parallel to the line on the graph paper;
- c) place a glass slide vertically over the left half (1,0 mm) of the nickel piece. Use a line of the graph paper as a guide to position the edge of the glass slide;