

PD IEC/TS 61244-1:2014



BSI Standards Publication

Determination of long-term radiation ageing in polymers

Part 1: Techniques for monitoring diffusion-limited oxidation

bsi.

...making excellence a habit.™

National foreword

This Published Document is the UK implementation of IEC/TS 61244-1:2014. It supersedes BS 7816-1:1995 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee GEL/112, Evaluation and qualification of electrical insulating materials and systems.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014.
Published by BSI Standards Limited 2014

ISBN 978 0 580 84311 2
ICS 17.240; 29.035.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 30 September 2014.

Amendments/corrigenda issued since publication

Date	Text affected
-------------	----------------------

SPECIFICATION TECHNIQUE



**Determination of long-term radiation ageing in polymers –
Part 1: Techniques for monitoring diffusion-limited oxidation**

**Détermination du vieillissement à long terme sous rayonnement dans les
polymères –
Partie 1: Techniques pour contrôler l'oxydation limitée par diffusion**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX



ICS 17.240; 29.035.01

ISBN 978-2-8322-1827-3

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Profiling techniques to monitor diffusion-limited oxidation	7
2.1 General.....	7
2.2 Infra-red profiling techniques	7
2.3 Modulus profiling.....	10
2.4 Density profiling	14
2.5 Miscellaneous profiling techniques	16
3 Theoretical treatments of diffusion-limited oxidation	18
4 Permeation measurements	21
5 Oxygen consumption measurements	21
6 Comparison of theory with experimental results.....	22
7 Oxygen overpressure technique.....	23
8 Summary.....	25
Annex A (informative) Derivation of theoretical treatment of diffusion-limited oxidation	26
A.1 General.....	26
A.2 Numerical simulation	29
A.3 Cylindrical and spherical geometries and simulation.....	30
A.4 Time dependence of the simulation.....	35
Bibliography	37
Figure 1 – Relative oxidation as determined from the carbonyl absorbance versus depth away from air-exposed surface of polyolefin material after ageing for 6 days at 100 °C (from [18]).....	8
Figure 2 – Depth distribution of carbonyl groups in irradiated (0,69 Gy/s) multilayer samples composed of 4, 18, 27 and 44 films of 22 µm thickness	9
Figure 3 – Micro-FTIR spectrophotometric determination of photoproduct and of residual double-bond profiles in a SBR film photooxidized for 100 h.....	10
Figure 4 – Schematic diagram of modulus profiling apparatus.....	11
Figure 5 – Modulus profiles of 1,68 mm thick commercial fluoro elastomer samples after air ageing at 5,49 kGy/h and 70 °C to the indicated radiation doses (from [15])	12
Figure 6 – Modulus profiles of 1,68 mm thick commercial fluoro elastomer samples after air ageing at 0,90 kGy/h and 70 °C to the indicated radiation doses (from [15])	12
Figure 7 – Modulus profiles of 1,68 mm thick commercial fluoro elastomer samples after air ageing at 0,14 kGy/h and 70 °C to the indicated radiation doses (from [15])	13
Figure 8 – Modulus profiles of 1,9 mm thick chloroprene rubber samples following elevated temperature exposures in the presence of air at 150 °C, left plot, and 100 °C, right plot (from [10]).....	13
Figure 9 – Experimental density profiles (crosses) for 0,302 cm (left) and 0,18 cm (right) thick EPDM sheets after ageing at 6,65 kGy/h and 70 °C in airX-ray microanalysis.....	14
Figure 10 – Effect of total radiation dose on XMA profile for 2 mm thick EPDM sheet irradiated at 1 kGy/h in air (from [24]).....	15

Figure 11 – XMA profiles of 1 mm thick EPDM sheets after thermal ageing in air (from [24])	16
Figure 12 – NMR self-diffusion coefficients versus distance away from sample surface for low-density polyethylene samples after gamma-irradiation in air or vacuum at 0,6 Gy/sec for the indicated total doses (from [26])	17
Figure 13 – Chemiluminescence profile for a polypropylene material after gamma irradiation in air to 0,05 MGy at 2 kGy/h (data from [30])	17
Figure 14 – Theoretical oxidation profiles for various values of α (indicated in the figure) with $\beta = 0,1$	19
Figure 15 – Identical to Figure 14, except that $\beta = 10$	20
Figure 16 – Identical to Figure 14, except that $\beta = 1\ 000$	20
Figure 17 – Plot of $\alpha_c/(\beta + 1)$ versus β , where α_c denotes the value of integrated oxidation corresponding to 90 % (from [7, 23])	21
Figure 18 – Apparatus used for irradiation under pressurized oxygen conditions	24
Figure 19 – Tensile elongation (left) and tensile strength (right) data for an EPR material aged at the indicated high and low dose-rates in air and at high dose rate in the pressurized oxygen apparatus of Figure 18	25
Figure A.1 – Simplified kinetic scheme used to represent the oxidation of polymers (from [44, 45])	26
Figure A.2 – Typical example of normalized concentration of oxygen for cylindrical shape for $\beta=0,01$ from [46]	31
Figure A.3 – Typical example of relative oxygen consumption for cylindrical shape for $\beta=0,01$ from [46]	31
Figure A.4 – Typical example of normalized concentration of oxygen for cylindrical shape for $\beta=100$ from [46]	32
Figure A.5 – Typical example of relative oxygen consumption for cylindrical shape for $\beta=100$ [46]	32
Figure A.6 – Typical example of normalized concentration of oxygen for spherical shape for $\beta=0,01$ from [46]	33
Figure A.7 – Typical example of relative oxygen consumption for spherical shape for $\beta=0,01$ from [46]	33
Figure A.8 – Typical example of normalized concentration of oxygen for spherical shape for $\beta=100$ from [46]	34
Figure A.9 – Typical example of relative oxygen consumption for spherical shape for $\beta=100$ [46]	34
Figure A.10 – Typical example of time-dependent normalized concentration of oxygen at the centre from for the case of $\beta=1$ [46]	35
Figure A.11 – Typical example of time-dependent normalized concentration of oxygen at the centre from for the case of $\alpha=50$ [46]	36

INTERNATIONAL ELECTROTECHNICAL COMMISSION

DETERMINATION OF LONG-TERM RADIATION AGEING IN POLYMERS –**Part 1: Techniques for monitoring diffusion-limited oxidation**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a technical specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC TS 61244-1, which is a technical specification, has been prepared by IEC technical committee 112: Evaluation and qualification of electrical insulating materials and systems.

This second edition cancels and replaces the first edition published in 1993 and constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) numerical simulation of DLO is much improved;
- b) geometry of samples has been expanded from only the case of the infinite plane to the cylindrical and the spherical cases.

The text of this specification is based on the following documents:

Enquiry draft	Report on voting
112/287/DTS	112/304/RVC

Full information on the voting for the approval of this technical specification can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 61244 series, published under the general title *Determination of long-term ageing in polymers*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- transformed into an International standard,
- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

It is usually necessary to estimate the anticipated lifetime of a polymeric material in various usage environments. For extended lifetimes (years), this often requires the application of accelerated ageing techniques which typically involve the modelling of results obtained at higher-than-ambient environmental stress levels. For many practical applications, air is present during environmental exposures – this usually implies that important oxidation effects underlie the degradation of the material. Unfortunately, exposure of polymers to air during ageing often results in inhomogeneously oxidized samples, a complication which affects attempts both to understand the oxidation process and to extrapolate accelerated exposures to long-term conditions.

The most important inhomogeneous oxidation complication involves diffusion-limited oxidation. The significance of this complication in various environments, including thermal [1]¹ radiation [2 to 4] and ultraviolet [5] has been recognized for many years. Diffusion-limited oxidation can occur whenever the rate of oxygen consumption in a material is greater than the rate at which oxygen can be resupplied to the interior of the material by diffusion processes from the surrounding air atmosphere. Such instances result in a smooth drop in the oxygen concentration from its equilibrium sorption value at the sample surfaces to a diminished or non-existent value in the sample interior. This will usually lead to a heterogeneity in the oxidation across the material, with equilibrium oxidation (e.g. corresponding to air-saturated conditions) occurring at the sample surfaces, and reduced or little oxidation in the interior.

The importance of the effect will clearly depend upon the material geometry, coupled with the oxygen consumption rate, the oxygen permeability coefficient and the oxygen partial pressure surrounding the sample [5 to 8]. Since the oxygen consumption rate will typically depend upon the environmental stress level (e.g. temperature, radiation dose rate) and both the consumption rate and the permeability coefficient may change as the material degrades [9, 10], the importance of diffusion-limited oxidation will also vary with stress level and degradation. This often implies that the percentage of the sample which is oxidized under accelerated (higher-level) environmental conditions is substantially lower than the percentage oxidized under lower-level application conditions [5 to 7, 10 to 16]. Thus, as has been clear for many years, in order to confidently extrapolate shorter-term accelerated simulations to long-term, air-ageing conditions, a critical requirement is the ability to monitor and quantitatively understand diffusion-limited oxidation effects.

Since a great deal of progress has recently been made in this area, this goal is now realistic. The purpose of this specification is to review this area. Clause 2 describes experimental profiling methods which can be used to monitor diffusion-limited oxidation. Theoretical descriptions of the phenomenon are briefly given in Clause 3. Since the shapes of the theoretical profiles depend upon the oxygen permeability coefficient and the oxygen consumption rate, these quantities are measured or estimated in order to quantitatively validate the theories. Many experimental methods have been developed for measuring permeability coefficients and a large number of experimental values are available in the literature. Clause 4 introduces some of the important literature. Experimental methods for estimating oxygen consumption rates is briefly reviewed in Clause 5. Experimental data supporting the theoretical treatments is presented in Clause 6. Once confidence in the theoretical treatments exists, the theories can be used either to choose experimental ageing conditions so that diffusion effects are unimportant, or to predict the importance of such effects. If it is impossible to eliminate diffusion effects under air ageing conditions, increasing the oxygen pressure surrounding the sample during ageing may, in certain instances, be used to achieve the desired goal, as outlined in Clause 7 on the oxygen overpressure technique.

Part 2 is published as a separate specification and describes procedures for predicting radiation ageing at low dose rates.

¹ Figures in square brackets refer to the Bibliography.

DETERMINATION OF LONG-TERM RADIATION AGEING IN POLYMERS –

Part 1: Techniques for monitoring diffusion-limited oxidation

1 Scope

This part of IEC TS 61244, which is a technical specification, reviews experimental techniques to quantitatively monitor the effects when oxygen is present during ageing of polymers in various environments including temperature, radiation or ultraviolet.

Inhomogenous ageing effects caused by diffusion-limited oxidation are often encountered and provide theoretical equations to estimate their importance. These effects make it difficult to understand the ageing process and to extrapolate accelerated exposure to long-term conditions.

It is widely known that mechanical properties degrade prior to electrical properties. These changes are consequences of chemical changes such as oxidation. In this technical specification, only mechanical or chemical monitoring techniques are of interest.

This technical specification does not deal with electrical monitoring techniques.

2 Profiling techniques to monitor diffusion-limited oxidation

2.1 General

The presence of diffusion-limited oxidation effects implies that various properties related to the amount of oxidation will depend upon spatial location in the material. Thus, any technique which can profile (map) these spatial variations will allow diffusion-limited oxidation to be monitored. Since polymer geometries utilize cross-sections down to a few millimetres or less, and since diffusion-limited oxidation effects are operative over such small dimensions, a useful profiling technique has to have a resolution of at least 100 μm . An additional problem related to sensitivity is the observation that severe polymer degradation typically corresponds to less than 1 % of the polymer being oxidized. Thus, a useful profiling technique shall have reasonable resolution, good sensitivity to the small chemical changes which occur, wide applicability and relative ease of operation and analysis. A number of particularly useful techniques are briefly described in this clause.

2.2 Infra-red profiling techniques

Because of the ability to provide detailed chemical information on thin film samples, infra-red spectroscopy has been used to monitor diffusion-limited oxidation effects for more than 25 years [17]. Any oxidation-sensitive infra-red peak that can be monitored, either as a function of sample thickness, or as a function of sequentially microtomed slices, will yield information on oxidation heterogeneities. Many of the studies to date have concentrated on the carbonyl region (approximately $1\,720\text{ cm}^{-1}$) of polyolefin materials, such as polyethylene and polypropylene, since infra-red peaks in this region are characterized by high extinction coefficients (high sensitivities) and are usually absent from these materials when unaged. Since the carbonyl region typically represents a superposition of a number of oxidation products (e.g. ketones, aldehydes, esters, acids) of differing extinction coefficients at slightly different wavelengths, simplifying assumptions are often needed to extract semi-quantitative information. In most cases, either the maximum height of the hybrid carbonyl peak or its area is chosen. It should be noted that additives present in commercially formulated materials (e.g. antioxidants, fire retardants) often absorb in the carbonyl region, thereby complicating attempts to use FTIR spectrometry for these materials.