

PD CEN/TS 12633:2014



BSI Standards Publication

Method of polishing specimens prior to the measurement of slip and skid resistance

bsi.

...making excellence a habit.™

National foreword

This Published Document is the UK implementation of CEN/TS 12633:2014. It supersedes DD ENV 12633:2003 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/507/7, Pedestrian slip resistance.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 81969 8

ICS 93.080.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 30 September 2014.

Amendments issued since publication

Date	Text affected
------	---------------

English Version

**Method of polishing specimens prior to the measurement of slip
and skid resistance**

Méthode de détermination de la valeur de résistance au
dérapage/à la glissance d'unités de pavage polies ou non
polies

Verfahren zur Bestimmung des Griffigkeitsbeiwertes vor
und nach Polierung

This Technical Specification (CEN/TS) was approved by CEN on 10 September 2013 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	Page
Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Principle.....	5
4 Apparatus	5
5 Sampling of test specimens	8
6 Preparation of test specimen	8
7 Polishing procedure	9
8 Validation of polishing procedure.....	9
9 Test report	10
Annex A (informative) Preparation of reference material specimens.....	11
A.1 Reference material.....	11
A.2 Apparatus and equipment	11
A.3 Preparation of reference material specimens.....	12
Bibliography.....	13

Foreword

This document (CEN/TS 12633:2014) has been prepared by Technical Committee CEN/TC 178 “Paving units and kerbs”, the secretariat of which is held by BSI.

This document supersedes ENV 12633:2003.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom

Introduction

Health and safety aspects

WARNING: The application of emery polishing agents during the course of the operations described in this Technical Specification can generate particles that could be injurious to health. It is essential to ensure that appropriate precautions are taken, e.g. the use of dust masks and/or dust extracting facilities. It is also essential to ensure that the equipment is electrically safe in wet test conditions.

1 Scope

This Technical Specification describes a laboratory method for polishing paving units using a flat-bed polishing machine prior to the measurement of slip and skid resistance to evaluate the durability of this characteristic. This Technical Specification may not be applicable to profiled paving units: for these types of units the method of polishing does not reflect the polishing in practice.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 772-20, *Methods of test for masonry units - Part 20: Determination of flatness of faces of aggregate concrete, manufactured stone and natural stone masonry units*

EN 772-1, *Methods of test for masonry units - Part 1: Determination of compressive strength*

ISO 48, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD)*

3 Principle

The Technical Specification describes the test method for polishing paving units using an abrasive agent in contact with a rotating resilient mat.

4 Apparatus

4.1 Straight-edge

4.2 Set of feeler gauges with a width of (6 ± 1) mm capable of measuring with an accuracy to 0,05 mm

4.3 Flat-bed polishing machine (see Figure 1) comprising the following: