



BSI Standards Publication

**Geosynthetic barriers
— Test method for the
determination of the influence
of wetting-drying cycles
on the permeability of clay
geosynthetic barriers**

National foreword

This Published Document is the UK implementation of CEN/TS 14417:2014. It supersedes DD CEN/TS 14417:2005 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/553, Geotextiles and geomembranes.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 85549 8

ICS 59.080.70

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 October 2014.

Amendments issued since publication

Date	Text affected
------	---------------

English Version

Geosynthetic barriers - Test method for the determination of the influence of wetting-drying cycles on the permeability of clay geosynthetic barriers

Géosynthétiques bentonitiques - Méthode d'essai pour la détermination de l'influence de cycles humidification/dessiccation sur la perméabilité des géosynthétiques bentonitiques

Geosynthetische Dichtungsbahnen - Prüfverfahren zur Bestimmung des Einflusses von Nass-Trocken-Zyklen auf die Wasserdurchlässigkeit von geosynthetischen Tondichtungsbahnen

This Technical Specification (CEN/TS) was approved by CEN on 21 July 2014 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword.....		3
Introduction		4
1 Scope		5
2 Normative references		5
3 Terms and definitions		5
4 Principle		5
5 Apparatus		5
6 Reagent.....		6
7 Procedure		6
7.1 Specimen preparation		6
7.2 Specimen hydration		6
7.3 Specimen drying.....		7
7.4 Specimen cooling		7
7.5 Repetition		7
7.6 Preparation of specimen for flux testing.....		7
8 Calculation and expression of results.....		8
8.1 Recording of data		8
8.2 Calculation and expression of results.....		8
9 Test report		8

Foreword

This document (CEN/TS 14417:2014) has been prepared by Technical Committee CEN/TC 189 "Geosynthetics", the secretariat of which is held by NBN.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 14417:2005.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This Technical Specification defines a method for testing the influence ratio of wetting-drying cycles on the flux through clay geosynthetic barriers. Such resistance is a requirement for many uses of these products.

The influence ratio is an indication of the behaviour of the product when exposed to repeated wetting and drying cycles in earth constructions. The flux of saturated clay geosynthetic barriers may increase after exposure to repeated wetting-drying cycles.

The Technical Specification does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and to comply with any regulations or legislation regardless of the wording in the technical specification.

The flux determined using this test method is not considered to be representative of the in-service flux of clay geosynthetic barriers. This test determines the influence of wetting-drying cycles in the absence of any other phenomenon, for example cation exchange.

1 Scope

This Technical Specification describes an index test to determine the influence ratio of wetting-drying cycles on the flux through saturated clay geosynthetic barrier specimens.

This test method is applicable to GBR-C products with no additional sealing layers attached.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 16416, *Geosynthetic clay barriers — Determination of water flux index — Flexible wall permeameter method at constant head*

EN ISO 3696, *Water for analytical laboratory use — Specification and test methods (ISO 3696)*

EN ISO 10320, *Geotextiles and geotextile-related products — Identification on site (ISO 10320)*

ISO 554, *Standard atmospheres for conditioning and/or testing — Specifications*

3 Terms and definitions

For the purposes of this document, the following term and definition applies.

3.1

influence ratio

ratio of the flux of a specimen exposed to wetting-drying cycles to that of the flux through an unexposed reference specimen, expressed in percent

4 Principle

The flux through 100 mm diameter clay geosynthetic barrier (GBR-C) specimens is determined with a flexible wall permeameter both on a specimen exposed to wetting-drying cycles and on an unexposed reference specimen.

A specimen either square with an edge length not less than 200 mm or circular with a diameter not less than 200 mm to a tolerance of $\pm 0,5$ % is saturated under a pressure of $(4 \pm 0,2)$ kPa for 48 h at constant room temperature. After saturation, the sample is dried under a pressure of $(4 \pm 0,2)$ kPa in an oven at 110 °C for 24 h. After the drying period the sample is allowed to cool to room temperature under a pressure of $(4 \pm 0,2)$ kPa for a minimum of 24 h. This wetting-drying cycle is performed four times before cutting the test specimen.

Test this specimen and the unexposed reference specimen in accordance with EN 16416.

5 Apparatus

The apparatus shall consist of the following:

- a template of known dimensions to a tolerance of $\pm 0,5$ % either square with an edge length not less than 200 mm or circular with a diameter not less than 200 mm,
- a waterproof box large enough to accommodate the specimen,