



Metallic Materials Properties Development and Standardization (MMPDS)

MMPDS-09

Chapter 9 – Guidelines

April 2014

Scientific Source:

Metallic Materials design data acceptable to Government procuring or certification agencies.

A joint effort of government, industrial, educational, and international aerospace organizations.

MMPDS-09

Copyright 2014 Battelle Memorial Institute. All rights reserved. Unauthorized duplication or distribution may violate the Copyright Laws of the United States and of other jurisdictions.

Except as expressly provided below, the copyrighted work contained herein may not be copied, modified, adapted, translated, included in derivative works or transferred to a third party. The information may be subject to export control laws and regulations of the United States. The user represents and warrants that the information will not be exported, transferred, sublicensed, copied, shared, disclosed, or used in any way except in compliance with all applicable export control laws and regulations of the United States.

The owner of this copy of the Handbook is hereby granted a limited license to make copies of no more than 10 individual pages of the Handbook (but specifically not including multiple sections or volumes) from this copy at a time for the sole purpose of attaching as reference and supporting information to a document authored by the owner.

The user of this Handbook assumes the responsibility for the selection of material properties from it to meet their requirements. The information contained herein is provided as-is without warranty. There are no warranties of any kind, either express or implied, including but not limited to the implied warranties of merchantability and fitness for a particular purpose.

FOREWORD

The Metallic Materials Properties Development and Standardization (MMPDS) Handbook, is an accepted source for metallic material and fastener system allowables recognized by the Federal Aviation Administration (FAA), all Departments and Agencies of the Department of Defense (DoD), and the National Aeronautics and Space Administration (NASA) within the limitations of the certification requirements of the specific government agency. Some of these limitations are noted below.

Federal Aviation Administration (FAA):

Per guidance provided by FAA Advisory Circular (AC) 25.613-1 and FAA policy memorandum PS-AIR100-2006-MMPDS, the ‘A’ and ‘B’ basis values published for materials in the MMPDS have been determined by the FAA to satisfy the material strength probability levels required by Title 14 of the Code of Federal Regulations (14 CFR) §§ 27.613(d), § 29.613(d), §25.613(b) and § 23.613(b). These values can be used to demonstrate compliance with the static strength requirements of 14 CFR without further showing. Other data provided (e.g. S-basis properties, fatigue, crack growth, stress-strain curves) in the Handbook might be used for design following FAA ACs and policy. The final determination on their applicability rests with the civil aviation authority responsible for finding compliance for the particular aircraft system on a case-by-case basis.

Department of Defense (DoD):

Per guidance provided in the Joint Service Specification Guide (JSSG) 2006 and MIL-STD-1530, the “A” and “B” basis design allowables published for materials in the MMPDS have been determined by Department of Defense (DoD) services to satisfy the strength and statistical variability requirements for airframe metallic materials. Other data (e.g. S-basis properties, fatigue, crack growth, stress-strain curves) in the Handbook may be used for design. However, the final determination of the acceptability of data rests with the cognizant design authority responsible for finding compliance for the particular aircraft system.

National Aeronautics and Space Agency (NASA):

The “A” and “B” basis design allowables published in the MMPDS handbook have been accepted by the National Aeronautics and Space Agency (NASA) as satisfying the strength requirements for metallic materials used in spacecraft and launch vehicles, as tailored in NASA-STD-6016. Other data (e.g. S-basis properties, fatigue, stress-strain curves) in the Handbook may be used for design. However, the final determination of the acceptability of data rests with the NASA design authority responsible for the particular system.

MMPDS-09 supersedes MMPDS-08 and prior editions of the MMPDS Handbook as well as all editions of MIL-HDBK-5, Metallic Materials and Elements for Aerospace Vehicle Structures Handbook that was maintained by the U.S. Air Force. The last edition, MIL-HDBK-5J was cancelled by the U.S. Air Force in March 2006.

This document contains design information on the mechanical and physical properties of metallic materials and joints commonly used in aircraft and aerospace vehicle structures. All information contained in this Handbook has been reviewed and approved using a standardized process. The development and

MMPDS-09
1 April 2014

ongoing maintenance process involves certifying agencies, including the FAA, DoD, and NASA, and major material suppliers and material users worldwide. The information and procedures in this Handbook are continuously reviewed, and modified or removed as determined to be appropriate. With advances in materials and fastener systems, and with the review process of existing information, periodic updates of the MMPDS should be expected. As such, it is recommended that the latest version of the MMPDS be used.

The allowables contained in the published document, or from approved minutes of the Metallic Materials Properties Development and Standardization (MMPDS) handbook coordination meetings, are acceptable to the Federal Aviation Administration (FAA), the Department of Defense (DoD), and the National Aeronautics and Space Administration (NASA), per the conditions as outlined above. The minutes are copyright protected and are considered approved 30 days after release of meeting minutes, if no objections or corrections have been received by Battelle, or 30 days after a technical change. Approval by the procuring or certifying agency must be obtained for the use of design values for products not contained herein.

Beneficial comments (recommendations, additions, deletions) and any pertinent data that may be of use in improving this document should be addressed to Secretariat, MMPDS Coordination Activity (614-424-6496 voice or bcommpds@battelle.org email), Battelle, MMPDS, 505 King Avenue, Columbus, OH 43201. You may also contact the Secretariat through the handbook website, www.mmpds.org.

This Handbook has been approved for public release with unlimited distribution.

Preparing activity:
FAA - William J. Hughes Technical Center

EXPLANATION OF NUMERICAL CODE

For chapters containing materials properties, a deci-numeric system is used to identify sections of text, tables, and illustrations. This system is explained in the examples shown below. Variations of this deci-numerical system are also used in Chapters 1, 8, and 9.

Example A 2.4.2.1.1

General material category (in this case, steel).....			
A logical breakdown of the base material by family characteristics (in this case, intermediate alloy steels); or for element properties.....			
Particular alloy to which all data are pertinent. If zero, section contains comments on the family characteristics.....			
If zero, section contains comments specific to the alloy; if it is an integer, the number identifies a specific temper or condition (heat treatment).....			
Type of graphical data presented on a given figure (see following description).....			

Example B 3.2.3.1.X

Aluminum.....			
2000 Series Wrought Alloy.....			
2024 Alloy.....			
T3, T351, T3510, T3511, T4, and T42 Tempers.....			
Specific Property as Follows.....			
Tensile properties (ultimate and yield strength).....			1
Compressive yield and shear ultimate strengths.....			2
Bearing properties (ultimate and yield strength).....			3
Modulus of elasticity, shear modulus.....			4
Elongation, total strain at failure, and reduction of area.....			5
Stress-strain curves, tangent-modulus curves.....			6
Creep.....			7
Fatigue.....			8
Fatigue-Crack Propagation.....			9
Fracture Toughness.....			10

This page is intentionally blank.

REGISTERED TRADEMARKS

<u>Trademark</u>	<u>Registered by</u>	<u>Chemistry</u>	<u>UNS Number</u>
15-5PH®	AK STEEL CORP.	15Cr - 4.6Ni - 0.22Cb - 2.8Cu	J92110
		15Cr - 4.5Ni - 0.30Cb - 3.5Cu	S15500
17-4-PH® ¹	ARMCO INC. CORP.	16Cr - 4.1Ni - 0.28Cb - 3.2Cu	J92200
		16.5Cr - 4.0Ni - 4.0Cu - 0.30Cb	S17400
17-7PH®	ARMCO INC. CORP.	17Cr-7.1Ni-1.1Al	J17700
ACRES® sleeves	CLICK BOND, INC.	NA	NA
AerMet® 100	CRS HOLDINGS INC.	3.1Cr-11.5Ni-13.5Co-1.2Mo (0.21 - 0.25C)	K92580
AM-350™	ALLEGHENY LUDLUM CORP.	16.5Cr - 4.5Ni - 2.9Mo - 0.10N	S35000
AM-355™	ALLEGHENY LUDLUM CORP.	15.5Cr - 4.5Ni - 2.0Mo - 0.10N	S35500
Cherry®	TEXTRON FASTENING SYSTEMS, INC.	NA	NA
Cherrybucks®	TEXTRON FASTENING SYSTEMS, INC.	NA	NA
Custom450®	CRS HOLDINGS INC.	15Cr - 6.5Ni - 0.75Mo - 0.30 (Cb + Ta) - 1.5Cu	S45000
Custom455®	CRS HOLDINGS INC.	12Cr-8.5Ni-2.0Cu-1.1Ti	S45500
Custom465®	CRS HOLDINGS INC.	6Al- 6V - 2SN	none
Ferrium® S53®	QUES TEK INNOVATIONS LLC	10Cr-5.5Ni-14Co-2Mo-1W (0.19-0.23C)	S10500
Ferrium® M54™	QUES TEK INNOVATIONS LLC	1Cr-10Ni-7Co-2Mo-1.3W (0.28-0.32C)	K91973
Hastelloy® X	HAYNES INTERNATIONAL, INC.	47.5Ni-22Cr-1.5Co-9.0Mo	N06002
Elektron® 21	MAGNESIUM ELEKTRON	EV31A	Similar to M12310
HAYNES®	HAYNES INTERNATIONAL, INC.	NA	NA
230®	HAYNES INTERNATIONAL, INC.	59Ni-22Cr-2Mo-14W-0.35Al	N06230
Hi-Lok®	HI-SHEAR CORP.	NA	NA
Hi-Shear®	HI-SHEAR CORP.	NA	NA
HR-120®	HAYNES INTERNATIONAL, INC.	35Fe - 24Cr - 37Ni - 0.65Cb - 0.2N	N08120
HSL180™	HITACHI METALS AND SUMITOMO PRECISION PRODUCTS	12.5Cr-1.0Ni-15.5Co-2.0Mo	NA

¹ Shown in the customary form of 17-4PH in the Handbook.

MMPDS-09
1 April 2014

<u>Trademark</u>	<u>Registered by</u>	<u>Chemistry</u>	<u>UNS Number</u>
INCONEL®	HUNTINGTON ALLOYS CORP.	NA	NA
MP159®	SPS TECHNOLOGY	19Cr - 36Co - 25Ni - 7.0Mo - 0.50Cb - 2.9Ti - 0.20Al - 9.0Fe	R30159
MP35N®	SPS TECHNOLOGY	20Cr - 35Ni - 35Co - 10Mo	R30035
PH13-8® Mo	ARMCO INC. CORP.	13Cr-8.0Ni-2.2Ni-1.1Al	S13800
PH15-7® Mo	ARMCO INC. CORP.	15Cr - 7.1Ni - 2.5Mo - 1.1Al	S15700
RENE´® 41	TELEDYNE INDUSTRIES INC.	54Ni - 19Cr - 11Co - 9.8Mo - 3.2Ti - 1.5Al - 0.006B	N0704
ToughMet® 3	MATERION BRUSH INC.	77Cu-15Ni-8Sn	C72900

CHAPTER 9 CONTENTS

GUIDELINES FOR THE PRESENTATION OF DATA

This chapter contains Guidelines for judging adequacy of data, procedures for analyzing data in determining property values for inclusion in previous chapters, and formats for submitting results of analyses to the MMPDS Coordination Group for approval. The index that follows should be helpful in locating sections of these Guidelines applicable to specific properties:

<u>Section</u>	<u>Page</u>
9.1 GENERAL INFORMATION	1
9.1.1 Introduction	1
9.1.2 Cross Index	1
9.1.3 Applicability	1
9.1.4 Approval Procedures	1
9.1.5 Documentation Requirements	1
9.1.6 Summary	4
9.1.7 Data Basis	6
9.1.8 Rounding Procedures	8
9.2 MATERIAL, SPECIFICATION, TESTING, AND DATA REQUIREMENTS	9
9.2.1 Material Requirements	9
9.2.2 Specification Requirements	9
9.2.3 Required Test Methods/ Procedures	9
9.2.3.1 Mechanical-Property Terms	12
9.2.3.2 Testing Direction and Specimen Location	12
9.2.3.3 Tension, Compression, Shear and Bearing	14
9.2.3.4 Other Static Properties	14
9.2.3.5 Required Test Methods to Determine Dynamic and Time Dependent Properties	15
9.2.3.6 Mechanically Fastened Joints	21
9.2.3.7 Fusion-Welded Joints	22
9.2.4 Data Requirements	23
9.2.4.1 S-Basis Values	23
9.2.4.2 A- and B-Basis Values	24
9.2.4.3 Derived Property Values	29
9.2.4.4 Other Static Properties	30

CHAPTER 9 CONTENTS

<u>Section</u>	<u>Page</u>
9.2.4.5 Data Requirements for Determination of Dynamic and Time Dependent Properties.....	32
9.2.4.6 Mechanically Fastened Joints	35
9.2.4.7 Fastener Strength Table Sunset Clause	39
9.2.4.8 Fusion-Welded Joints.....	46
9.2.5 Experimental Design	46
9.2.5.1 Uniformity of Sample Size across Thickness Range	46
9.2.5.2 Fatigue.....	47
9.2.5.3 Creep-Rupture.....	53
9.2.5.4 Fusion-Welded Joints.....	55
9.3 SUBMISSION OF DATA	57
9.3.1 Recommended Procedures	57
9.3.2 Computer Software.....	57
9.3.3 Introductory Section	57
9.3.4 General Data Formats.....	57
9.3.4.1 Data Format for the Computation of T99 and T90 Values	58
9.3.4.2 Data Format for Derived Properties.....	58
9.3.4.3 Data Format for the Construction of Typical Stress-Strain Curves	62
9.3.4.4 Data Format for Fasteners.....	62
9.3.4.5 Data Format for Other Properties.....	63
9.4 SUBSTANTIATION OF PROPERTIES.....	67
9.4.1 S-Basis Minimum Properties.....	67
9.4.2 Validating Design Properties for Existing Materials (When a Change in Processing 00s Occurred).....	68
9.4.3 Confirmation of Design Properties for Legacy Alloys.....	69
9.4.3.1 Initial Steps and Analysis.....	69
9.4.3.2 Increase in Design Properties.....	69
9.4.3.3 Decrease in Design Properties	70
9.4.3.4 Derived Properties.....	70

CHAPTER 9 CONTENTS

<u>Section</u>	<u>Page</u>
9.5 ANALYSIS PROCEDURES FOR STATISTICALLY COMPUTED MINIMUM STATIC PROPERTIES.....	75
9.5.1 Specifying the Population.....	75
9.5.1.1 Deciding Between Direct and Indirect Computation.....	75
9.5.1.2 Testing for Regression Effects and homogeneity.....	78
9.5.1.3 Data Transformation.....	82
9.5.2 Regression Analysis	90
9.5.2.1 Linear Regression.....	90
9.5.2.2 Quadratic Regression.....	92
9.5.2.3 Tests for Adequacy of a Regression	95
9.5.2.4 Testing for Equality of Several Regressions	97
9.5.3 Combinability of Data	100
9.5.3.1 The k-Sample Anderson-Darling Test.....	100
9.5.3.2 The F Test.....	102
9.5.3.3 The t Test.....	103
9.5.4 Determining the Form of Distribution.....	105
9.5.4.1 “Anderson-Darling” Test for Normality.....	105
9.5.4.2 Normal Probability Plot.....	106
9.5.4.3 Three-Parameter Weibull Acceptability Test.....	106
9.5.4.4 Modified Anderson-Darling Test for Pearsonality	108
9.5.4.5 The Pearson Backoff Option	109
9.5.4.6 Pearson Probability Plot	109
9.5.4.7 Modified “Anderson-Darling” Test for Weibullness	112
9.5.4.8 The Weibull Backoff Option	114
9.5.4.9 Weibull Probability Plots	115
9.5.4.10 Detection of Lower-Tail Truncation.....	117
9.5.5 Direct Computation without Regression	119
9.5.5.1 Sequential Pearson Procedure	124
9.5.5.2. Sequential Weibull Procedure	125
9.5.5.3 Nonparametric Procedure.....	126

CHAPTER 9 CONTENTS

<u>Section</u>	<u>Page</u>
9.5.6 Direct Computation by Regression Analysis.....	127
9.5.6.1 Performing the Regression.....	127
9.5.7 Indirect Computation without Regression (Reduced Ratios/ Derived Properties	129
9.5.7.1 Treatment of Grain Direction	129
9.5.7.2 Treatment of Test Specimen Location.....	130
9.5.7.3 Treatment of Clad Aluminum Alloy Plate	130
9.5.7.4 Computational Procedure	131
9.5.8 Indirect Computation Using Regression.....	132
9.5.9 Handling of Derived Property Test Results below Estimated Design Allowable	133
9.5.10 Indirect Computation of Edgewise Bearing Reductions.....	135
9.6 ANALYSIS PROCEDURES FOR DYNAMIC AND TIME DEPENDENT PROPERTIES	137
9.6.1 Load and Strain Control Fatigue Data	137
9.6.1.1 Data Collection and Interpretation	140
9.6.1.2 Analysis of Data	141
9.6.1.3 Fatigue Life Models	142
9.6.1.4 Evaluation of Mean Stress and Strain Effects	144
9.6.1.5 Estimation of Fatigue-Life Model Parameters	145
9.6.1.6 Treatment of Outliers	151
9.6.1.7 Assessment of the Fatigue Life Model.....	152
9.6.1.8 Data Set Combination.....	154
9.6.1.9 Treatment of Runouts.....	155
9.6.1.10 Recognition of Time Dependent Effects	156
9.6.2 Fatigue Crack Growth Data	157
9.6.2.1 Data Collection and Interpretation	158
9.6.3 Fracture Toughness Data	160
9.6.3.1 Plane-Strain Fracture Toughness Data	160
9.6.3.1.1 Data Collection and Interpretation.....	160
9.6.3.2 Plane Stress and Transitional Fracture Toughness	161
9.6.3.3 Crack Resistance (R-Curve).....	162

CHAPTER 9 CONTENTS

<u>Section</u>	<u>Page</u>
9.6.4 Creep and Creep-Rupture Data.....	168
9.6.4.1 Data Collection and Interpretation.....	168
9.6.4.2 Analysis of Data.....	170
9.7 ANALYSIS PROCEDURES FOR STRUCTURAL JOINT PROPERTIES	175
9.7.1 Mechanically Fastened Joints	175
9.7.1.1 Definitions	176
9.7.1.2 Yield Load Determination	177
9.7.1.3 Shear Strength of Fastener	182
9.7.1.4 Sheet Critical and Transition Critical Strengths	183
9.7.1.5 Calculation of Allowable Loads	202
9.7.2 Fusion-Welded Joint Data	204
9.7.2.1 Data Collection and Interpretation.....	204
9.7.2.2 Data Analysis.....	206
9.8 Examples of Data Analysis and Data Presentation for Static Properties.....	207
9.8.1 Direct Analyses of Mechanical Properties	207
9.8.2 Indirect Analyses of Mechanical Properties	220
9.8.3 Tabular Data Presentation	224
9.8.3.1 Mechanical Properties.....	224
9.8.3.2 Modulus of Elasticity and Poisson's Ratio	229
9.8.3.3 Physical Properties.....	230
9.8.4 Room Temperature Graphical Mechanical Property Data	230
9.8.4.1 Typical Stress-Strain.....	230
9.8.4.2 Compression-Tangent-Modulus Curves	241
9.8.4.3 Full-Range Tensile Stress-Strain Curves	244
9.8.4.4 Minimum Stress-Strain and Stress Tangent-Modulus Curves.....	249
9.8.4.5 Biaxial Stress-Strain Behavior.....	249
9.8.4.6 Mathematical Representation of Stress-Strain Curves.....	250
9.8.5 Elevated Temperature Graphical Mechanical Properties	253
9.8.5.1 Strength Properties.....	253

CHAPTER 9 CONTENTS

<u>Section</u>	<u>Page</u>
9.8.5.2 Elongation and Reduction of Area.....	265
9.8.5.3 Modulus of Elasticity.....	265
9.8.5.4 Physical Properties.....	266
9.8.5.5 Effect of Thermal Exposure on Room Temperature Strength.....	267
9.8.5.6 Effect of Thermal Exposure on Elevated Temperature Strength.....	268
9.8.5.7 Simple Exposure.....	269
9.8.5.8 Complex Exposure.....	270
9.9 EXAMPLES OF DATA FOR DYNAMIC AND TIME DEPENDANT PROPERTIES.....	273
9.9.1 Fatigue.....	273
9.9.1.1 Load Control.....	279
9.9.1.2 Strain Control.....	287
9.9.2 Fatigue Crack Growth.....	290
9.9.3 Fracture Toughness.....	296
9.9.3.1 Plane Strain.....	296
9.9.3.2 Plane Stress.....	296
9.9.4 Creep and Creep Rupture.....	297
9.9.4.1 Creep-Rupture Example Problem.....	298
9.9.5 Mechanically Fastened Joints.....	304
9.9.5.1 Example Analysis Problem for Three Diameter Blind Fastener Dataset.....	310
9.9.6 Fusion-Welded Joints.....	347
9.9.6.1 Additional Information.....	347
9.9.6.2 Room-Temperature Properties.....	347
9.9.6.3 Data on Effect of Temperature.....	348
9.9.6.4 Use of Design Data.....	349
9.10 STATISTICAL TABLES.....	351
REFERENCES.....	373