



**STANDARD FOR
EXTRUDED INSULATION POWER CABLES
RATED ABOVE 46 THROUGH 345 KV**

Approved by

AMERICAN NATIONAL STANDARDS INSTITUTE

November 27, 2012

Publication # ANSI/ICEA S-108-720-2012

© 2012 by ICEA

INSULATED CABLE ENGINEERS ASSOCIATION, Inc

STANDARD FOR
EXTRUDED INSULATION POWER CABLES
RATED ABOVE 46 THROUGH 345 KV

Standard
ICEA S-108-720-2012

Published By
INSULATED CABLE ENGINEERS ASSOCIATION, Inc.
Post Office Box 1568
Carrollton, Georgia 30112, U.S.A.

Approved by Insulated Cable Engineers Association, Inc.: June 6, 2012
Accepted by AEIC: Cable Engineering Committee: March 4, 2010
Approved by ANSI: November 27, 2012

Typographical error corrected in Table 9-3 on 3/6/13

© Copyright 2012 by the Insulated Cable Engineers Association, Inc. All rights including translation into other languages, reserved under the Universal Copyright Convention, the Berne Convention for the Protection of Literary and Artistic Works, and the international and Pan American Copyright Conventions.

FOREWORD

This Standards Publication for Extruded Insulation Power Cables Rated above 46 to 345 kV (ICEA S-108-720) was developed by the Insulated Cable Engineers Association Inc. (ICEA).

ICEA standards are adopted in the public interest and are designed to eliminate misunderstandings between the manufacturer and the purchaser and to assist the purchaser in selecting and obtaining the proper product for his particular need. Existence of an ICEA standard does not in any respect preclude the manufacture or use of products not conforming to the standard. The user of this Standards Publication is cautioned to observe any health or safety regulations and rules relative to the manufacture and use of cable made in conformity with this Standard.

Requests for interpretation of this Standard must be submitted in writing to the Insulated Cable Engineers Association, Inc., P. O. Box 1568, Carrollton, Georgia 30112. An official written interpretation will be provided. Suggestions for improvements gained in the use of this Standard will be welcomed by the Association.

The ICEA expresses thanks to the Association of Edison Illuminating Companies, Cable Engineering Committee for providing the basis for some of the material included herein through their participation in the Utility Power Cable Standards Technical Advisory Committee (UPCSTAC), and to the Institute of Electrical and Electronics Engineers, Insulated Conductors Committee, Subcommittee A, Discussion Group A-14 for providing user input to this Standard.

The members of the ICEA working group contributing to the writing of this Standard consisted of the following:

F. Kuchta, Chairman

E. Bartolucci
B. Crawford
L. Hiivala
A. Pack
B. Vaughn

R. Bristol
D. Elder
D. Masakowski
B. Temple
E. Walcott

J. Cancelosi
B. Fleming
K. Nuckles
R. Thrash

TABLE OF CONTENTS

Part 1 GENERAL 1

1.1 SCOPE..... 1

1.2 GENERAL INFORMATION 1

1.3 INFORMATION TO BE SUPPLIED BY PURCHASER..... 1

 1.3.1 Characteristics of Systems on which Cable is to be Used 1

 1.3.2 Description of Installation 2

 1.3.3 Quantities and Description of Cable..... 2

1.4 INFORMATION TO BE SUPPLIED BY MANUFACTURER 2

1.5 DEFINITIONS AND SYMBOLS..... 3

Part 2 CONDUCTOR 6

2.0 GENERAL 6

2.1 PHYSICAL AND ELECTRICAL PROPERTIES 6

 2.1.1 Copper Conductors 6

 2.1.2 Aluminum Conductors 6

 2.1.3 Special Conductors 6

 2.1.3.1 Segmental Conductors..... 7

2.2 OPTIONAL WATER BLOCKING COMPONENTS FOR STRANDED CONDUCTORS..... 7

2.3 CONDUCTOR SIZE UNITS 7

2.4 CONDUCTOR DC RESISTANCE 7

 2.4.1 Direct Measurement of dc Resistance Per Unit Length..... 8

 2.4.2 Calculation of dc Resistance Per Unit Length..... 8

2.5 CONDUCTOR DIAMETER 8

Part 3 CONDUCTOR SHIELD 14

3.1 MATERIAL 14

3.2 EXTRUDED CONDUCTOR SHIELD THICKNESS..... 14

3.3 PROTRUSIONS AND IRREGULARITIES 14

3.4 VOIDS 15

3.5 PHYSICAL REQUIREMENTS..... 15

3.6 ELECTRICAL REQUIREMENTS 15

 3.6.1 Extruded Semiconducting Material..... 15

 3.6.2 Extruded Nonconducting Material (For EPR Insulation Only) 15

 3.6.3 Semiconducting Tape 15

3.7 CROSSLINKED (THERMOSET) REQUIREMENTS..... 15

Part 4 INSULATION 16

4.1 MATERIAL 16

4.2 INSULATION THICKNESS 16

 4.2.1 Selection of Proper Thickness..... 17

 4.2.2 Insulation Eccentricity 18

4.3 INSULATION REQUIREMENTS..... 18

 4.3.1 Physical and Aging Requirements 18

 4.3.2 Electrical Test Requirements..... 19

 4.3.2.1 Partial-Discharge for Discharge-Free Designs only 19

 4.3.2.2 Voltage Tests..... 20

 4.3.2.3 Insulation Resistance Test 20

 4.3.2.4 Dielectric Constant and Dissipation Factor..... 21

 4.3.2.5 Discharge (Corona) Resistance for Discharge-Resistant EPR Designs only 21

4.3.3	Voids, Ambers, Gels, Agglomerates and Contaminants as Applicable	21
4.3.3.1	Crosslinked Polyethylene Insulation (XLPE)	21
4.3.3.2	Ethylene Propylene Rubber (EPR)	21
4.3.4	Shrinkback - Crosslinked Polyethylene Insulation (XLPE) Only	21
Part 5	EXTRUDED INSULATION SHIELD	23
5.1	MATERIAL	23
5.2	EXTRUDED INSULATION SHIELD THICKNESS	23
5.3	PROTRUSIONS AND IRREGULARITIES	23
5.4	VOIDS	23
5.5	PHYSICAL REQUIREMENTS	23
5.6	ELECTRICAL REQUIREMENTS	24
5.5.1	Extruded Semiconducting Material	24
5.5.2	Semiconducting Tape	24
5.7	CROSSLINKED (THERMOSET) REQUIREMENTS	24
Part 6	METALLIC SHIELDING	25
6.1	GENERAL	25
6.2	SHIELDS	25
6.2.1	Helically Applied Tape Shield	25
6.2.2	Longitudinally Applied And Overlapped Corrugated Tape Shield	25
6.2.3	Wire Shield	25
6.2.4	Flat Strap Shield	26
6.3	SHEATHS	26
6.3.1	Lead Sheath	26
6.3.2	Smooth Aluminum Sheath	26
6.3.3	Continuously Corrugated Sheath	26
6.4	RADIAL MOISTURE BARRIER	27
6.4.1	Bonded Metallic Foil Laminates	27
6.5	OPTIONAL LONGITUDINAL WATER BLOCKING COMPONENTS	27
Part 7	JACKET	28
7.1	MATERIAL	28
7.1.1	Polyethylene, Black	28
7.1.2	Polyvinyl Chloride	29
7.2	JACKET APPLICATION AND THICKNESS	30
7.2.1	Thickness of Jacket for Tape, Wire Shield and Metallic Foil Laminate	30
7.2.2	Thickness of Jacket for Sheaths	30
7.3	OPTIONAL SEMICONDUCTING COATING	30
7.4	JACKET IRREGULARITY INSPECTION	30
7.4.1	Jackets without Optional Semiconducting Coating	30
7.4.2	Jackets with Optional Semiconducting Coating	30
Part 8	CABLE IDENTIFICATION	33
8.1	CABLE IDENTIFICATION	33
8.1.1	Optional Center Strand Identification	33
8.1.2	Optional Sequential Length Marking	33
Part 9	PRODUCTION TESTS	34
9.1	TESTING	34
9.2	SAMPLING FREQUENCY	34
9.3	CONDUCTOR TEST METHODS	34

9.3.1	Method for DC Resistance Determination	34
9.3.2	Cross-Sectional Area Determination	34
9.3.3	Diameter Determination	34
9.4	TEST SAMPLES AND SPECIMENS FOR PHYSICAL AND AGING TESTS	34
9.4.1	General	34
9.4.2	Measurement of Thickness	34
9.4.2.1	Micrometer Measurements	35
9.4.2.2	Optical Measuring Device Measurements	35
9.4.3	Number of Test Specimens	35
9.4.4	Size of Specimens	35
9.4.5	Preparation of Specimens of Insulation and Jacket	36
9.4.6	Specimen for Aging Test	36
9.4.7	Calculation of Area of Test Specimens	36
9.4.8	Unaged Test Procedures	36
9.4.8.1	Test Temperature	36
9.4.8.2	Type of Testing Machine	36
9.4.8.3	Tensile Strength Test	37
9.4.8.4	Elongation Test	37
9.4.9	Aging Tests	37
9.4.9.1	Aging Test Specimens	37
9.4.9.2	Air Oven Test	38
9.4.9.3	Oil Immersion Test for Polyvinyl Chloride Jacket	38
9.4.10	Hot Creep Test	38
9.4.11	Solvent Extraction	38
9.4.12	Wafer Boil Test for Conductor and Insulation Shields	38
9.4.13	Amber, Agglomerate, Gel, Contaminant, Protrusion, Irregularity and Void Test	38
9.4.13.1	Sample Preparation	38
9.4.13.2	Examination	38
9.4.13.3	Resampling for Amber, Agglomerate, Gel, Contaminant, Protrusion, Irregularity and Void Test	39
9.4.13.4	Protrusion and Irregularity Measurement Procedure	39
9.4.14	Physical Tests for Semiconducting Material Intended for Extrusion	40
9.4.14.1	Test Sample	40
9.4.14.2	Test Specimens	40
9.4.14.3	Elongation	40
9.4.15	Retests for Physical and Aging Properties and Thickness	40
9.5	DIMENSIONAL MEASUREMENTS OF THE METALLIC SHIELD	40
9.5.1	Tape Shield	40
9.5.2	Wire Shield	40
9.5.3	Sheath	41
9.5.4	Flat Straps	41
9.6	DIAMETER MEASUREMENT OF INSULATION AND INSULATION SHIELD	41
9.7	TESTS FOR JACKETS	41
9.7.1	Heat Shock (PVC only)	41
9.7.1.1	Preparation of Test Specimen	41
9.7.1.2	Winding of the Test Specimen on Mandrels	41
9.7.1.3	Heating and Examination	42
9.7.2	Heat Distortion	42
9.7.3	Cold Elongation (PVC only)	42
9.7.3.1	Test Temperature	42
9.7.3.2	Type of Testing Machine	42
9.7.3.3	Elongation Test	42
9.8	VOLUME RESISTIVITY	43

9.8.1	Conductor Shield.....	43
9.8.2	Insulation Shield and Semiconducting Extruded Jacket Coating.....	43
9.8.3	Test Equipment.....	44
9.8.4	Test Procedure.....	44
9.9	SHRINKBACK TEST PROCEDURE.....	44
9.9.1	Sample Preparation.....	44
9.9.2	Test Procedure.....	44
9.9.3	Pass/Fail Criteria and Procedure.....	44
9.10	RETESTS ON SAMPLES.....	44
9.11	AC VOLTAGE TEST.....	45
9.11.1	General.....	45
9.11.2	AC Voltage Test.....	45
9.12	PARTIAL-DISCHARGE TEST PROCEDURE.....	45
9.13	METHOD FOR DETERMINING DIELECTRIC CONSTANT AND DIELECTRIC STRENGTH OF EXTRUDED NONCONDUCTING POLYMERIC STRESS CONTROL LAYERS.....	45
9.14	WATER CONTENT.....	46
9.14.1	Water Under the Jacket.....	46
9.14.2	Water in the Conductor.....	46
9.14.3	Water Expulsion Procedure.....	46
9.14.4	Presence of Water Test.....	46
9.15	ADHESION TESTS FOR METALLIC FOIL LAMINATES.....	46
9.15.1	Visual Inspection.....	46
9.15.2	Adhesion Strength of Metallic Foil Laminate.....	47
9.15.3	Adhesion Strength of Overlap of Metallic Foil Laminate.....	47
9.16	PRODUCTION TEST SAMPLING PLANS.....	49
Part 10	QUALIFICATION TESTS.....	52
10.0	GENERAL.....	52
10.1	CABLE QUALIFICATION TESTS.....	52
10.1.1	Cable Design Qualification.....	52
10.1.2	Cable Bending Procedure.....	55
10.1.2.1	Bending Diameter.....	55
10.1.3	Thermal Cycling Procedure.....	55
10.1.3.1	Thermal Cycles.....	55
10.1.3.2	Voltage During Thermal Cycles.....	56
10.1.4	Hot Impulse Test Procedure.....	56
10.1.5	AC Voltage Withstand Test Procedure.....	56
10.1.6	Partial Discharge Test Procedure (For Discharge-Free Designs Only).....	56
10.1.7	Measurement of Dissipation Factor.....	56
10.1.8	Dissection and Analysis of Test Specimens.....	57
10.2	JACKET MATERIAL QUALIFICATION TESTS.....	57
10.2.1	Polyethylene Jackets.....	57
10.2.1.1	Environmental Stress Cracking Test.....	57
10.2.1.1.1	Test Specimen.....	57
10.2.1.1.2	Test Procedure.....	57
10.2.1.2	Absorption Coefficient Test.....	57
10.2.2	Semiconducting Extruded Jacket Coatings.....	58
10.2.2.1	Brittleness Temperature.....	58
10.2.3	Polyvinyl Chloride.....	58
10.2.3.1	Sunlight Resistance.....	58
10.2.3.1.1	Test Samples.....	58
10.2.3.1.2	Test Procedure.....	58

10.3	OTHER QUALIFICATION TESTS	58
10.3.1	Insulation Resistance	58
10.3.2	Accelerated Water Absorption Tests	58
10.3.3	Resistance Stability Test	59
10.3.4	Brittleness Temperature for Semiconducting Shields	59
10.3.5	Discharge Resistance Test for Discharge-Resistant EPR Designs only	59
10.3.5.1	Test Specimens	59
10.3.5.2	Test Environment	59
10.3.5.3	Test Electrodes	60
10.3.6	Dielectric Constant and Voltage Withstand for Nonconducting Conductor Shield	60
Part 11	APPENDICES	61
APPENDIX A	NEMA, ICEA, IEEE, ASTM AND ANSI STANDARDS (Normative)	61
A1	NEMA PUBLICATIONS	61
A2	ICEA PUBLICATIONS	61
A3	IEEE AND ANSI STANDARDS	61
A4	ASTM STANDARDS	61
APPENDIX B	EMERGENCY OVERLOADS (Normative)	64
APPENDIX C	PROCEDURE FOR DETERMINING THICKNESS REQUIREMENTS OF THE INSULATION SHIELD, LEAD SHEATH AND JACKET (Normative)	67
APPENDIX D	CABLE COMPONENT FUNCTION (Informative)	69
D1	CONDUCTOR	69
D1.1	Function	69
D1.2	Material	69
D2	CONDUCTOR SHIELD	69
D2.1	Function	69
D2.1.1	Nonconducting	69
D2.1.2	Semiconducting	69
D2.2	Voltage Stress	69
D3	INSULATION	70
D4	INSULATION SHIELD	70
D4.1	Semiconducting Shield	71
D4.2	Metallic Shield	71
D5	JACKET	71
APPENDIX E	HANDLING AND INSTALLATION PARAMETERS (Informative)	73
E1	INSTALLATION TEMPERATURES	73
E2	RECOMMENDED MINIMUM BENDING RADIUS	73
E3	DRUM DIAMETERS OF REELS	73
E4	MAXIMUM TENSION AND SIDEWALL BEARING PRESSURES	73
E5	ELECTRICAL TESTS AFTER INSTALLATION	74
E5.1	Insulation	74
E5.2	Jacket	74
APPENDIX F	TRADITIONAL INSULATION WALL THICKNESS (Informative)	75
APPENDIX G	ADDITIONAL SHIELD WIRE AND CONDUCTOR INFORMATION (Informative)	76
APPENDIX H	ETHYLENE ALKENE COPOLYMER (EAM) (Informative)	79
APPENDIX I	SPECIFICATION FOR ALLOY LEAD SHEATHS (Informative)	80
I1	PURPOSE	80
I2	MATERIAL	80
I3	REQUIREMENTS	80
APPENDIX J	GUIDELINE FOR DEGASSING (Informative)	81
APPENDIX K	STRESS CALCULATION FOR EPR CABLES WITH A NONCONDUCTING CONDUCTOR SHIELD (Informative)	83

LIST OF TABLES

Table 2-1	Weight Increment Factors	8
Table 2-2	Nominal Direct Current Resistance in Ohms Per 1000 Feet at 25 °C of Concentric Lay Stranded and Segmental Conductor	9
Table 2-2 (Metric)	Nominal Direct Current Resistance in Milliohms Per Meter at 25 °C of Concentric Lay Stranded and Segmental Conductor	10
Table 2-3	Nominal Diameters for Round Copper and Aluminum Conductors	11
Table 2-3 (Metric)	Nominal Diameters for Round Copper and Aluminum Conductors	12
Table 2-4	Nominal Diameters for Segmental Copper and Aluminum Conductors	13
Table 2-5	Factors for Determining Nominal Resistance of Stranded Conductors Per 1000 Feet at 25 °C	13
Table 3-1	Extruded Conductor Shield Thickness	14
Table 4-1	Conductor Maximum Temperatures	16
Table 4-2	Conductor Sizes, Maximum Insulation Eccentricity, Insulation Maximum Stress and Test Voltages	18
Table 4-3	Insulation Physical Requirements	19
Table 4-4	Partial-Discharge Requirements	19
Table 4-5	Test Voltages for Partial-Discharge Measurements	20
Table 4-6	Impulse Values	20
Table 4-7	Dielectric Constant and Dissipation Factor	21
Table 4-8	Shrinkback Test Requirements	22
Table 5-1	Insulation Shield Thickness	23
Table 6-1	Lead Sheath Thickness	26
Table 7-1	Polyethylene, Black	28
Table 7-2	Polyvinyl Chloride	29
Table 7-3	Semiconducting Extruded Coating	31
Table 7-4	Jacket Thickness and Test Voltage for Tape, Wire Shield or Metallic Foil Laminate Cables	31
Table 7-5	Jacket Thickness and Test Voltage for All Sheath Cables	32
Table 9-1	Test Specimens for Physical and Aging Tests	35
Table 9-2	Bending Requirements for Heat Shock Test	42
Table 9-3	Summary of Production Tests and Sampling Frequency Requirements	49
Table 9-4	Plan E	51
Table 9-5	Plan F	51
Table 10-1	Generic Grouping of Cable Components	53
Table 10-2	Accelerated Water Absorption Properties	59
Table D-1	Jacket Functions	72
Table E-1	Recommended Minimum Bending Radius	73
Table F-1	Traditional Insulation Thickness from AIEC CS7-93, Test Voltages and Conductor Sizes	75
Table G-1	Solid Copper Shield Wires	76
Table G-2	Concentric Stranded Class B Aluminum and Copper Conductors	77
Table G-3	Concentric Stranded Class C and D Aluminum and Copper Conductors	78
Table I-1	Chemical Requirements for Alloy Lead Sheaths	80

Part 1 GENERAL

1.1 SCOPE

This standard applies to materials, constructions, and testing of crosslinked polyethylene (XLPE) and ethylene propylene rubber (EPR) insulated single conductor shielded power cables rated above 46 to 345 kV used for the transmission of electrical energy.

1.2 GENERAL INFORMATION

This publication is arranged to allow for selection of individual components (such as conductors, insulation, extruded shields, metallic shields, jackets, etc.) as required for specific installation and service conditions.

Parts 2 to 7 cover the major components of cables:

- Part 2 - Conductor
- Part 3 - Conductor Shield
- Part 4 - Insulation
- Part 5 - Extruded Insulation Shield
- Part 6 - Metallic Shielding
- Part 7 - Jacket

Each of these parts designates the materials, material characteristics, dimensions, and tests applicable to the particular component.

Part 8 covers identification of cables.

Part 9 covers production test procedures applicable to cable component materials and to completed cables.

Part 10 covers qualification test procedures.

Part 11 contains appendices of pertinent information.

U.S. customary units, except for temperature, are specified throughout this standard. Approximate International System of Units (SI) equivalents are included for information only.

1.3 INFORMATION TO BE SUPPLIED BY PURCHASER

When requesting proposals from cable manufacturers, the prospective purchaser should describe the cable desired by reference to pertinent provisions of these standards. To help avoid misunderstandings and possible misapplication of the cable, the purchaser should also furnish the following information:

1.3.1 Characteristics of Systems on which Cable is to be Used

- a. Desired ampacity for normal and emergency operation.
- b. Frequency.
- c. Nominal phase-to-phase operating voltage.
- d. Maximum phase-to-phase operating voltage.
- d. Basic Impulse Insulation Level (BIL).
- e. Symmetrical and asymmetrical fault current and duration for conductor and metallic shield/sheath.
- f. Daily load factor.