

*under revision see DR 85353*

AS 1178-1979

UDC 621.315.212.4:678.742.2

# Australian Standard 1178-1979

---

## CONCENTRIC WIRE NEUTRAL XLPE INSULATED CABLES FOR ELECTRICITY SUPPLY FOR WORKING VOLTAGES OF 0.6/1 kV

[Title allocated by Defence Cataloguing Authority:  
CABLE, POWER, ELECTRICAL (CONCENTRIC NEUTRAL, XLPE  
INSULATED, 0.6/1 kV)]



**STANDARDS ASSOCIATION OF AUSTRALIA**

*Incorporated by Royal Charter.*



THE FOLLOWING SCIENTIFIC, INDUSTRIAL AND GOVERNMENTAL ORGANIZATIONS and departments were officially represented on the committee entrusted with the preparation of this standard:

Australian-British Trade Association  
Australian Electrical and Electronic Manufacturers Association  
Confederation of Australian Industry  
Defence Standardization Committee  
Department of Construction  
Department of Transport  
Electrical Approvals Authorities  
Electrical Contractors Associations of Australia  
Electrical Testing Laboratories  
Electricity Supply Association of Australia  
Metals Industry Organizations  
Railways of Australia Committee  
Representative of SAA Committee EL/2  
Telecom Australia

---

This standard, prepared by Committee EL/3, Electric Wires and Cables, was approved on behalf of the Council of the Standards Association of Australia on 6 February 1979, and was published on 1 October 1979.

---

To keep abreast of progress in industry, Australian standards are subject to continuous review and are kept up-to-date by the issue of amendments or revised editions as necessary. It is important therefore that standards users ensure that their standards are up-to-date. Full details of all SAA publications will be found in the Annual List of Australian Standards; these details are supplemented by monthly listings in the SAA Monthly Information Sheet. Information on the Annual List and the SAA Monthly Information Sheet may be obtained from any sales office of the Association, where details are also available of the current status of individual standards.

---

*This standard was issued in draft form for public review as DR 77119.*

January 1980

STANDARDS ASSOCIATION OF AUSTRALIA

Incorporated by Royal Charter

**CORRIGENDA**

to

**AS 1178—1979**

**CONCENTRIC WIRE NEUTRAL XLPE INSULATED CABLES FOR ELECTRICITY SUPPLY  
FOR WORKING VOLTAGES OF 0.6/1 kV**

*SUMMARY:* The following sections of the standard are covered by this correction slip: Preface; Contents; Clauses 2.4, 9.3; Tables 1, 2; Clauses 12.1, 12.3; Tables 3, 4, 5; Appendix A; Appendix B; Appendix C; Appendix F.

Published on 1 February 1980.

22 JAN-1980

**AUSTRALIAN STANDARD**

**CONCENTRIC WIRE NEUTRAL  
XLPE INSULATED CABLES FOR  
ELECTRICITY SUPPLY FOR  
WORKING VOLTAGES OF  
0.6/1 kV**

**AS 1178—1979**

First published ..... 1979

**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA  
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**

**ISBN 0 7262 1658 5**

## PREFACE

This standard was prepared by the Association's Committee on Electric Wire and Cables. The cables specified herein are primarily intended for use by electricity supply authorities.

During the preparation of this standard, consideration was given to ESI\* standard 09-9, Polymeric Insulated, Combined Neutral/Earth (CNE) Cables with Solid Aluminium Phase Conductors and Concentric Aluminium Wire Waveform Neutral/Earth Conductor, issued by the EB/BEAMA/BSI Standards Policy Steering Committee† and acknowledgement is made of the assistance received therefrom.

The nominal cross-sectional areas of phase conductors specified herein are taken from AS 1125, Conductors in Insulated Electric Cables and Flexible Cords, and are identical with values recommended in IEC 228, Nominal Cross-sectional Areas and Composition of Conductors of Insulated Cables.

This standard differs from ESI 09-9 in that copper and copper-clad aluminium wires are specified in addition to aluminium for the concentric neutral conductor.

XLPE compound insulation is specified for the phase conductors and the thicknesses of insulation are in accordance with IEC recommendations. V-90 PVC compound has been specified for the cable oversheath and the thickness of the oversheath is in accordance with IEC recommendations.

This standard may require reference to the following standards:

- AS 1115 <sup>SEE AMENDMENT Corr. Jan. 1980</sup> Conductors in Insulated Electric Cables and Flexible Cords (Metric Units)
- AS 1660 Methods of Test for Electric Cables and Flexible Cords (Including Conductors, Insulation and Sheath)  
Part 1—Test Methods for Conductors  
Part 2—Test Methods for Insulation, Sheath and Braid  
Part 3—Test Methods for Complete Cable
- AS 3147 Approval and Test Specification for PVC Insulated Electric Cables and Flexible Cables for Working Voltages of 0.6/1 kV
- AS 3198 Approval and Test Specification for XLPE Insulated Electric Cables for Working Voltages of 0.6/1 kV
- BS 2627 Wrought Aluminium for Electrical Purposes—Wire

\*Electricity Supply Industry (of the United Kingdom).

†ESI standards are issued by the EB/BEAMA/BSI Standards Policy Committee under the authority and support of the Electricity Council, BEAMA and the Executive Board of the British Standards Institution. The various organizations comprising the ESI Standards Policy Steering Committee are:

EB, Electricity Board (British)

BEAMA, is the main federation of trade associations mentioned in the standardization of plant and equipment used by ESI.

BSI, British Standards Institution.

©Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1979

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

## CONTENTS

	<i>Page</i>
<b>SPECIFICATION</b>	
1 Scope .....	4
2 Definitions .....	4
3 Voltage Designation .....	4
4 Maximum Conductor Temperature .....	4
5 Conductors .....	4
6 Insulation of Phase Conductors .....	5
7 Identification of Cores .....	5
8 Laying up of Cores .....	5
9 Fillers, Tapes, Binders .....	5
10 Application of Concentric Neutral Conductor .....	5
11 Insulating Sheath .....	10
12 Cable Markings .....	10
13 Protection of Cable for Transportation and Installation .....	10
14 Marking of Cable Drums .....	10
15 Tests .....	10
16 Routine Tests at Works .....	12
17 Measurement of Thickness of Corrosion-preventive Layer .....	12
<b>TABLES</b>	
1 Details of 2-conductor (Single-core) Cables .....	7
2 Details of 4-conductor (3-core) Cables .....	8
3 Tests—Sequence, Criteria, Category and Reference .....	10
4 Spark Test Voltage for Cores .....	12
5 Spark Test Voltage for Insulating Sheath .....	12
<b>APPENDICES</b>	
A Method for Determination of Resistance to Water Penetration .....	13
B Method for Determination of Restriction of Corrosion of Concentric Neutral Conductors .....	15
C Method of Ageing <sup>Spec 1st</sup> Cables of the <del>Corrosion-preventive Layer</del> of Cables .....	16
D Recommendations for Sample Selection and Retest Procedure .....	17
E Recommendations for the Installation of Concentric Wire Neutral XLPE Insulated Cables .....	18
F Information Required with Enquiry and Order .....	19
G Colours of Manufacturers' Identification Threads .....	20

SEE AMENDMENT  
COTI. Jan. 1980.

## STANDARDS ASSOCIATION OF AUSTRALIA

## Australian Standard

for

## CONCENTRIC WIRE NEUTRAL XLPE INSULATED CABLES FOR ELECTRICITY SUPPLY FOR WORKING VOLTAGES OF 0.6/1 kV

**1 SCOPE.** This standard specifies the construction, dimensions and tests for concentric wire neutral cross-linked polyethylene (XLPE) insulated cables having two conductors (single core) or four conductors (3-core) and an insulating sheath, primarily for use by electricity supply authorities, at working voltages up to and including 0.6/1 kV.

NOTE: Cables covered by this standard should not be used in electrical installations unless approval has been obtained from the appropriate Regulatory or Statutory Authority.

**2 DEFINITIONS.** For the purpose of this standard the definitions in AS 1125 and the following definitions apply.

**2.1 Concentric wire neutral cable**—a cable with one or three cores, together with a concentric wire conductor which is used as a neutral or neutral/earth.

**2.2 Core of a cable**—a phase conductor and its own insulation (dielectric) but not including any protective covering.

**2.3 Direction of lay**—the direction of slope of a core or the like, when the cable is held vertically.

It is right hand when the slope is in the direction of the central part of the letter Z, and left hand when the slope is in the direction of the central part of the letter S.

**2.4 Wavelength**—the axial distance between successive crests of the waveform of the concentric neutral conductor. *SEE AMENDMENT corr. Jan. 1980*

**2.5 Maximum conductor temperature**—the maximum temperature at which the conductor of the cable may be operated under normal loading conditions, and is the temperature resulting from the combined effect of the ambient temperature and the current loading of the conductor.

**2.6 Voltage designation**—the rated voltages  $U_0$  and  $U$  expressed in the form  $U_0/U$ , where—

- $U_0$  is the r.m.s. power frequency voltage to earth of the supply system for which the cable is designed;
- $U$  is the r.m.s. power frequency voltage between phases of the supply system for which the cable is designed.

**2.7 Routine tests**—tests made by the manufacturer on all finished cable lengths to demonstrate the integrity of the cable.

**2.8 Special tests**—tests made by the manufacturer on samples of completed cables, at a specified frequency, so as to verify that the finished product meets the design specification.

**2.9 Type tests**—tests made by the manufacturer before supplying on a general commercial basis a type of cable covered by this standard, in order to demonstrate satisfactory performance characteristics

to meet the intended application. These tests are of such a nature that, after they have been made, they need not be repeated, unless changes are made in the cable materials or design which might change in performance characteristics.

**3 VOLTAGE DESIGNATION.** The rated voltage  $U_0/U$  recognized for the purposes of this standard is 0.6/1 kV.

**4 MAXIMUM CONDUCTOR TEMPERATURE.** The maximum conductor temperature of cables shall be 90°C.

## NOTES:

- The value of 90°C is based on the intrinsic properties of the insulating materials (including sheath) and is only valid if the installation conditions, cable connectors and other accessories are compatible with this temperature.
- For cables buried in the ground, it may be necessary to limit the maximum conductor temperature to a value considerably less than 90°C, unless the thermal condition of the soil in the dry condition is known and is used in the calculation of the current rating.

This limitation is recommended because of the risk of the drying out of the surrounding soil, causing an increase in thermal resistivity, which in turn would lead to the cable temperature rising to a higher temperature than anticipated.

**5 CONDUCTORS.**

**5.1 Phase Conductors.** Phase conductors shall be of aluminium in accordance with Section 3 of AS 1125 and shall comply with the following requirements, as appropriate:

- Conductors of nominal cross-sectional areas 25 mm<sup>2</sup>, 35 mm<sup>2</sup> and 50 mm<sup>2</sup> shall be circular, solid aluminium.
- Conductors of nominal cross-sectional areas 70 mm<sup>2</sup> to 300 mm<sup>2</sup> shall be shaped, solid aluminium.

**5.2 Concentric Neutral Conductor.**

**5.2.1 Material.** The concentric neutral conductor shall be of annealed copper, aluminium or copper-clad aluminium wires in accordance with AS 1125. Aluminium wires shall be of GIE material in the O condition, in accordance with BS 2627.

**5.2.2 Formation.** The number and diameter of wires in the concentric neutral conductor shall conform to the requirements of Table 1 or 2, as applicable. The wires shall be applied concentrically with a helical or waveform lay. The gap between wires shall not exceed 4 mm. Aluminium wires shall be evenly spaced and shall have a gap between adjacent wires.

The wavelength of the waveform lay shall be as follows:

- for 2-conductor cables shall be within  $\pm 10$  percent of the values given in Table 1, or a sub-multiple, at the manufacturer's discretion; and