

Australian Standard[®]

**METHODS FOR THE
TENSILE TESTING OF METALS
AT ELEVATED TEMPERATURES**

The following scientific, industrial and governmental organizations and departments were officially represented on the committee entrusted with the preparation of this standard:

Aluminium Development Council
Australasian Institute of Metals
Bureau of Steel Manufacturers of Australia
Commonwealth Scientific and Industrial Research Organization
Confederation of Australian Industry
Department of Defence
Federal Chamber of Automotive Industries
Metal Trades Industry Association of Australia
National Association of Testing Authorities
Railways of Australia Committee
Society of Automotive Engineers — Australasia
University of Melbourne
University of Sydney

This standard, prepared by Committee MT/6, Mechanical Testing of Metals, was approved by the Metals Standards Board on behalf of the Council of the Standards Association of Australia on 4 June 1979, and was published on 1 October 1979.

Review of Australian Standards. *To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.*

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This standard was issued in draft form for public review as DR 78017.

Australian Standard[®]

**METHODS FOR THE
TENSILE TESTING OF METALS
AT ELEVATED TEMPERATURES**

First published 1979

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 1757 3

PREFACE

This standard was prepared by the Association's Committee on the Mechanical Testing of Metals under the direction of the Metal Standards Board.

During preparation of the standard, the committee considered BS 3688: 1963, Methods for Mechanical Testing of Metals at Elevated Temperatures, Part 1 — Tensile Testing, and ASTM E21, Recommended Practice for Elevated Temperature Tension Tests for Metallic Materials.

As far as practicable the standard has been aligned with AS 1391, Methods for Tensile Testing of Metals.

Generally, proof stress and yield stress are the most important properties of metals determined at high temperatures. However, as many laboratories carry out tests to determine the tensile strength, the elongation and the percentage reduction of area, provisions for determining these properties have been included in the standard.

This standard requires reference to the following Australian and British standards:

AS 1545 Methods for the Calibration and Grading of Extensometers

AS 2193 Methods for Calibration and Grading of Force-measuring Systems of Testing Machines

BS 1041 Code for Temperature Measurement

BS 3894 Method for Converting Elongation Values for Steel.

CONTENTS

	<i>Page</i>		<i>Page</i>
FOREWORD	3	14 Determination of Tensile Strength (R_m)	11
METHODS		15 Determination of Percentage Elongation After Fracture	11
1 Scope	3	16 Determination of Percentage Reduction of Area	11
2 Definitions	3	17 Record of Results	11
3 Symbols and Designations	4	18 Report	12
4 Test Pieces	4		
5 Selection and Preparation of Test Pieces	5	APPENDICES	
6 Cross-sectional Area	8	A Guidance on Heating and Temperature Measurement	13
7 Original Gauge Length	9	B Observations on Force/Extension Diagrams	14
8 Method of Gripping	9	C Guidance on the Design and Use of Heating Apparatus	16
9 Accuracy of Testing Equipment	9	D Record of Results	17
10 Heating of the Test Piece	10	E Guidance for Product Standards Drafting Committees	18
11 Straining of the Test Piece	10		
12 Determination of Yield Stresses	11		
13 Determination of Proof Stress	11		

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard
METHODS FOR THE TENSILE TESTING OF METALS
AT ELEVATED TEMPERATURES

FOREWORD

Dimensions for test pieces specified in this standard have been selected in the interests of standardization. It should not be assumed that geometrically similar round test pieces or rectangular test pieces always give comparable values of ductility.

METHODS

1 SCOPE. This standard sets out methods by which a test piece of metal is strained in uni-axial tension at elevated temperature in order to determine one or more of its tensile properties. It defines the properties to be determined and the terms used in describing tests and test pieces. It specifies the dimensions of standard test pieces, temperature requirements and methods of tensile testing.

This standard does not specify the properties to be determined; these are stated in the product specification.

2 DEFINITIONS. For the purpose of this standard, the following definitions apply (see also Clause 3 and the appropriate figures):

2.1 Test sample—a portion of material or product or a group of items selected from a batch or consignment by a sampling procedure.

2.2 Test specimen—a portion or a single item taken from the test sample for the purpose of applying a particular test.

2.3 Test piece—a prepared piece for testing, made from a test specimen by some mechanical operation.

2.4 Gauge length—the prescribed part of the cylindrical or prismatic portion of the test piece, i.e. test section, on which extension is measured.

2.4.1 Original gauge length (L_o)—the gauge length at room temperature before the test piece is strained.

2.4.2 Final gauge length (L_u)—the gauge length at room temperature after the test piece has been fractured and the fractured parts have been carefully fitted together so that they lie in a straight line.

2.4.3 Extensometer gauge length (L_e)—the original length at room temperature of the parallel portion

of the test piece used for the measurement of the extension by means of an extensometer.

NOTE: The length may differ from L_o and may be of any value greater than b or $2d$ (see Clause 3), but must not be more than $L_e - 0.5 \sqrt{S_o}$.

2.4.4 Extensometer equivalent elastic gauge length (L_q)—the parallel length at room temperature which would give the same elastic extension as that determined experimentally by an extensometer attached to the reference marks on the enlarged ends of the test piece.

2.4.5 Modified parallel gauge length (L_m)—the length of the reduced section of the test piece between the points on the transition radii at which the mean diameter (or width) is 1.05 times the mean diameter (or mean width) of the parallel section.

2.5 Strain—the increase of length per unit length.

2.5.1 Nominal strain—the increase in length, at any moment during the test, divided by the original unit length.

NOTE: Strain does not include thermal expansion.

2.6 Extension—the increase of the gauge length.

NOTE: Extension does not include thermal expansion.

2.7 Elongation—extension expressed as a percentage of the original gauge length (see Clause 7.4).

2.7.1 Percentage elongation after fracture (A)—the extension after fracture ($L_u - L_o$), expressed as a percentage of the original gauge length (L_o).

2.8 Percentage reduction of area after fracture (Z)—the maximum change in cross-sectional area ($S_o - S_u$) measured after fracture, expressed as a percentage of the original cross-sectional area (S_o), where (S_u) is the minimum cross-sectional area after fracture, the measurements being made at room temperature.

2.9 Maximum force (F_m)—the greatest force which the test piece withstands during the test.