


Please be aware that this PDF has been created from the original hardcopy document, which might not be in good condition and so the PDF might reflect this.



No. 24—PART 5—1925.

British Standards Institution
Incorporated by Royal Charter
FORMERLY
British Engineering Standards Association

FORMED IN 1901 AS THE ENGINEERING STANDARDS COMMITTEE.

BRITISH
STANDARD SPECIFICATIONS
FOR
RAILWAY ROLLING STOCK MATERIAL.
PART 5.
COPPER PLATES, RODS, TUBES AND PIPES
AND BRASS TUBES.

(REVISED 1924 and 1925.)

LONDON:
PUBLISHED BY THE BRITISH STANDARDS INSTITUTION,
PUBLICATIONS DEPARTMENT,
28, VICTORIA STREET, LONDON, S.W.1.
Telegrams: Standards, Sovesel, London. Telephone: Abbey 8333.

February, 1925.

COPYRIGHT.

ALL RIGHTS RESERVED, INCLUDING RIGHTS OF TRANSLATION.

Price 2/- Net. Post Free 2/6.

The following Government Departments and Scientific and Industrial Organisations were represented upon the Sectional Committees, Sub-Committees and Panels entrusted with the preparation of these Specifications:—

Admiralty.
War Office.
India Office.
Air Ministry.
Crown Agents for the Colonies.
Board of Trade.
General Post Office.
National Physical Laboratory.
Institution of Mechanical Engineers.
Institution of Automobile Engineers.
Institute of Metals.
Association of Consulting Engineers.
Association of Railway Locomotive Engineers.
Incorporated Municipal Electrical Association.
Lloyd's Register of Shipping.
Railway Companies' Association.
British Non-Ferrous Metals Research Association.
Association of British Motor Manufacturers.
Brass and Copper Tube Association.
Brass Wire Association.
Brassfounders' Employers' Association.
British Electrical and Allied Manufacturers' Association.
Cold Rolled Brass and Copper Association.
High Conductivity Copper Association.
Iron and Steel Trades Employers' Association.
Locomotive Manufacturers' Association.
Manufactured Copper Association.
Society of British Aircraft Constructors, Ltd.
Society of Motor Manufacturers and Traders, Ltd.
Steel Founders' Association of Great Britain.

Specifications Nos. 11 and 12 were adopted by the Sectional Committee on Non-Ferrous Alloys at their meeting on 11th February, 1924, and by the Sectional Committee on Locomotives at their meeting on 17th March, 1924. They were approved on behalf of the Main Committee on 19th July, 1924.

Specification No. 12a was adopted by the Sectional Committee on Non-Ferrous Alloys in April, 1924, and approved on behalf of the Sectional Committee on Locomotives on 24th July, 1924. It was approved on behalf of the Main Committee on 19th November, 1924. Specifications Nos. 13, 14 and 15 were approved on behalf of the Sectional Committee on Non-Ferrous Alloys and the Sectional Committee on Locomotives in January, 1925. They were approved on behalf of the Main Committee on 2nd February, 1925.

NOTE.

In order to keep abreast of progress in the Industries concerned, the British Standard Specifications are subject to periodical review. Suggestions for improvements, addressed to the Director, British Engineering Standards Association, 28, Victoria Street, London, S.W.1, will be welcomed at all times. They will be recorded, and in due course brought to the notice of the Committees charged with the revision of the Specifications to which they refer.

No. 24—PART 5—1925.

British Standards Institution
Incorporated by Royal Charter
FORMERLY
British Engineering Standards Association

FORMED IN 1901 AS THE ENGINEERING STANDARDS COMMITTEE.

BRITISH
STANDARD SPECIFICATIONS
FOR
RAILWAY ROLLING STOCK MATERIAL.

PART 5.
COPPER PLATES, RODS, TUBES AND PIPES,
AND BRASS TUBES.

(REVISED 1924 and 1925.)

LONDON:
PUBLISHED BY THE BRITISH STANDARDS INSTITUTION,
PUBLICATIONS DEPARTMENT,
28 VICTORIA STREET, LONDON, S.W.1.
Telegrams: Standards, Sowest, London. Telephone: Abbey 9988.

February, 1925.

COPYRIGHT.

ALL RIGHTS RESERVED. INCLUDING RIGHTS OF TRANSLATION.

Price 2/- Net. Post Free 2/2.

CONTENTS.

| | PAGE |
|--|------|
| No. 11—1924. Copper Plates for Locomotive Fire Boxes... | 3 |
| No. 12—1924. Rolled Copper Rods for Locomotive Stay Bolts, Rivets, etc. ... | 5 |
| No. 12a—1924. Extruded Copper Rods for Locomotive Stay Bolts, Rivets, etc. ... | 7 |
| No. 13—1925. Copper Tubes for Locomotive Boilers ... | 9 |
| No. 14—1925. Brass Tubes for Locomotive Boilers ... | 12 |
| No. 15—1925. Seamless Copper Pipes for Locomotives ... | 15 |

APPENDIX.

| | |
|---|----|
| Forms of British Standard Tensile Test Pieces ... | 19 |
|---|----|

OTHER PARTS OF REPORT No. 24.

| |
|---|
| PART 1—1921. Locomotive, Carriage and Wagon Axles. |
| PART 2—1921. Locomotive, Carriage and Wagon Tyres. |
| PART 3—1921. Laminated, Volute and Helical Springs and Steel for Laminated Springs. |
| PART 4—1921. Steel Forgings, Blooms and Castings. |
| PART 6—1921. Steel Plates, Angles, etc., and Rivets for Locomotives, Carriages and Wagons. |

Reference to be quoted.

| |
|----------------------------------|
| Report No. 24 |
| Specification No. 11-1924 |

NOTE.—The Association desires to call attention to the fact that this Specification is intended to include the technical provisions necessary for the supply of the material herein referred to, but does not purport to include all the necessary provisions of a Contract.

**BRITISH
STANDARD SPECIFICATION FOR**

COPPER PLATES

FOR

LOCOMOTIVE FIRE BOXES.

(REVISED 1924).

The figures in British measures are to be regarded as the Standard. Approximate metric equivalents are given for the convenience of users in countries in which the metric system has been generally adopted.

Quality of Material.

1. The Plates shall contain not less than 99.20 per cent of copper, and shall contain not less than 0.30 per cent nor more than 0.50 per cent of arsenic.

The Manufacturer shall supply an analysis when required to do so.

Freedom from Defects.

2. The Plates shall be clean, smooth, free from surface defects, and shall be thoroughly annealed.

Marking.

3. Each Plate shall be stamped with the Manufacturer's name and plate number, about 12 inches (say 300 mm.) from the end in the centre line of the Plate, and shall also be distinctly stamped with such marks of identification as the Engineer (or the Purchaser) may require.

Mechanical Tests.

4. The scrap margin before shearing shall be not less than 30 inches (76.20 mm.) at each end, and 1½ inches (38.10 mm.) at each side of the Plate; from this margin a piece at each end 2 inches (50.80 mm.) wide shall be left attached to the Plate, from which the representative of the Engineer (or of the Purchaser) will mark lengths for tensile and bend tests. All test pieces shall comply with the following mechanical tests without further heat treatment.

(4)

Tensile Test.

5. A Standard Test Piece **A** (see Appendix, page 20) shall show a tensile breaking strength of not less than 14 tons (31,360 lb.) per square inch (22 kg. per mm.²), with an elongation of not less than 35 per cent.

5

End Test.

6. Test pieces shall be taken from the piece 2 inches (50.80 mm.) wide, described in Clause 4, and tested both cold and at a red heat by the ends being bent through an angle of 180° in opposite directions as shown in Fig. 1, and doubled up close, without showing either crack or flaw on the outside of either bend. The edges of the test pieces shall be draw-filed to remove roughness and sharpness.




Fig. 1.

Additional Tests before Rejection.

7. Should any of the test pieces first selected by the representative of the Engineer (or of the Purchaser) fail to pass the chemical or mechanical tests, two further test pieces from the same Plate shall be selected for testing. Should either of these test pieces so selected fail as to the requirements of either the chemical or mechanical tests, the Plates represented by the test pieces shall be liable to rejection.

20

Inspection.

8. The representative of the Engineer (or the Purchaser) shall be at liberty to reject any material that does not conform to the terms of this Specification. He will attend to stamp pieces for testing before delivery, and no Plate will be accepted which will not stand the specified tests or which upon analysis is found not to conform to the limits stated for the chemical composition.

Testing Facilities.

9. The Manufacturer shall supply the material required for testing free of charge and shall, at his own cost, furnish and prepare the necessary test pieces, and supply labour and appliances for such testing as may be carried out on his premises in accordance with this Specification. Failing facilities at his own works for making the prescribed tests, the Manufacturer shall bear the cost of carrying out the tests elsewhere.

35

(5)

NOTE.—The Association desires to call attention to the fact that this Specification is intended to include the technical provisions necessary for the supply of the material herein referred to, but does not purport to include all the necessary provisions of a Contract.

5

BRITISH**STANDARD SPECIFICATION**

FOR

ROLLED COPPER RODS

FOR

**LOCOMOTIVE STAY BOLTS, RIVETS, 10
ETC.**

(REVISED 1924).

The figures in British measures are to be regarded as the Standard. Approximate metric equivalents are given for the convenience of users in countries in which the metric system has been generally adopted.

15

Quality of Material.

1. The Rods shall contain not less than 99.20 per cent of copper, and shall contain not less than 0.30 per cent nor more than 0.50 per cent of arsenic.

The Manufacturer shall supply an analysis when required to do so.

Freedom from Defects.

2. The Rods shall be clean, smooth, uniform in diameter and free from surface defects. The character of the material shall be ascertained by breaking off a small portion from one Rod in twenty-five. The material shall be free from piping or other defects of every description.

Marking.

3. Each Rod shall be stamped with the Manufacturer's name near one end.

30

Mechanical Tests.

4. The representative of the Engineer (or of the Purchaser) shall select and test such of the Rods as he may think proper up to two per cent. of each diameter of Rod ordered under the contract.

35

All test pieces shall withstand the following mechanical tests in the annealed condition, but, in the case of Rods ordered annealed, without any further heat treatment.

Tensile Test.

5. The tensile strength shall be not less than 14.50 tons (32,480 lb.) per square inch (23 kg. per mm.²), with an elongation