



BSI Standards Publication

Optical fibre cables — Shrinkage effects on cable and cable element end termination — Guidance

National foreword

This Published Document is the UK implementation of IEC TR 62959:2021.

The UK participation in its preparation was entrusted to Technical Committee GEL/86/1, Optical fibres and cables.

A list of organizations represented on this committee can be obtained on request to its committee manager.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2021
Published by BSI Standards Limited 2021

ISBN 978 0 539 03183 6

ICS 33.180.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 March 2021.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------



TECHNICAL REPORT



Optical fibre cables – Shrinkage effects on cable and cable element end termination – Guidance

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 33.180.10

ISBN 978-2-8322-9434-5

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	7
INTRODUCTION.....	9
1 Scope.....	10
2 Normative references	10
3 Terms and definitions	10
4 Abbreviated terms	11
5 Characteristics of optical fibre cables	11
5.1 General.....	11
5.2 Cable materials.....	11
5.2.1 Plastic materials	11
5.2.2 Reversible thermal expansion and contraction	11
5.2.3 Irreversible thermal contraction (shrinkage)	12
5.2.4 Forces between cable elements caused by thermal changes	13
5.3 Cable design.....	13
5.4 Basic cable types.....	14
5.5 Cable performance	15
5.5.1 General	15
5.5.2 Optical performance during temperature changes	15
5.5.3 Cable shrinkage characteristic.....	16
5.5.4 Cable shrinkage during connector termination process	16
6 Test methods for cable shrinkage	17
6.1 General.....	17
6.2 Conditions before shrinkage testing	17
6.3 Test method F11.....	17
6.4 Test method F17.....	18
7 Conclusions of the cable shrinkage study	19
7.1 General.....	19
7.2 Conclusion for simplex cables.....	19
7.3 Conclusion for loose tube cables	20
8 Termination cases of optical fibre cables	20
8.1 General.....	20
8.2 Different termination cases	20
9 Recommended tests for evaluation of shrinkage effects.....	21
9.1 General.....	21
9.2 Limitation of tests for determination of shrinkage effects	22
9.3 Cables terminated with connectors.....	22
9.3.1 Performance indicator tests	22
9.3.2 Cable shrinkage.....	22
9.3.3 Cable thermal expansion and contraction	22
9.3.4 Cable element forces.....	22
9.4 Cables terminated with hardened connectors	22
9.4.1 Performance indicator tests	22
9.4.2 Cable shrinkage (fibre protrusion).....	23
9.5 Cables fixed into a module and fibres terminated with connectors.....	23
9.5.1 Performance indicator tests	23
9.5.2 Cable shrinkage (fibre protrusion).....	23

9.6	Cables fixed into a divider and fan-out cables terminated with connectors	23
9.6.1	Performance indicator tests	23
9.6.2	General	24
9.6.3	Shrinkage (fibre protrusion)	24
9.6.4	Shrinkage of fan-out cable	24
9.7	Cables fixed into a protective housing and terminated with splices	25
9.7.1	Performance indicator tests	25
9.7.2	Cable shrinkage (fibre protrusion)	25
9.7.3	Sheath shrinkage	25
9.8	Cables fixed into a protective housing and terminated with connectors	25
9.8.1	Performance indicator tests	25
9.8.2	Cable shrinkage	25
10	Recommended test parameters for shrinkage testing and shrinkage grades	26
10.1	General	26
10.2	Recommended test parameters for shrinkage testing	26
10.3	Shrinkage grades for Method F11A	27
10.4	Recommended shrinkage limit for Method F11B	27
10.5	Fibre protrusion grades for Method F17	27
Annex A (informative)	Test results of the cable shrinkage study	29
A.1	General	29
A.2	Shrinkage test results of simplex cables	29
A.2.1	Simplex cable types for shrinkage tests	29
A.2.2	Shrinkage test with different aging methods and duration	29
A.2.3	Shrinkage test with various numbers of temperature cycles	33
A.2.4	Shrinkage test with different sample lengths	34
A.2.5	Shrinkage test versus optical performance of two different simplex cables	34
A.2.6	Shrinkage test versus optical performance of different versions of a simplex cable	36
A.2.7	Change in length during and after climatic exposure	36
A.3	Shrinkage test results for loose tube cables	37
A.3.1	Loose tube cable types for shrinkage tests	37
A.3.2	Shrinkage test (method F11 modified) of four loose tube cable types	37
A.3.3	Shrinkage test (method F17) of four loose tube cable types	39
A.3.4	Shrinkage test of nine unitube cable types	43
Annex B (informative)	Test method for change in length during climatic exposure	45
B.1	General	45
B.2	Cable samples	45
B.3	Apparatus for determination of the change in length	45
B.4	Procedure for determination of the change in length	46
B.5	Test results for the change in length	46
B.6	Procedure for determination of the change in attenuation	47
B.7	Test results for the change in attenuation	47
B.8	Comparison of change in length with change in attenuation	50
B.9	Conclusion	51
Annex C (informative)	Shrinkage testing template	52
Annex D (informative)	Recommended tests for performance evaluation of cables to be terminated with connectors	53
D.1	General	53

D.2	Connector types and design.....	53
D.3	Simplex and duplex cable types	55
D.4	Termination of a cable to a connector	56
D.5	Overview of recommended cable tests	57
D.6	Main performance of a terminated cable	57
D.7	Guidance for change of temperature test methods	58
Annex E (informative) Recommended tests for performance evaluation of cables to be terminated with hardened connectors.....		59
E.1	General.....	59
E.2	Connector types and design.....	59
E.3	Cable types for hardened connectors	59
E.4	Termination of a cable to a hardened connector.....	59
E.5	Overview of recommended cable tests	60
E.6	Environmental performance of a terminated cable.....	60
Annex F (informative) Recommended tests for performance evaluation of cables fixed into a module and fibres terminated with connectors		61
F.1	General.....	61
F.2	Connector types and design.....	61
F.3	Cable types.....	61
F.4	Termination of a cable to a module	61
F.5	Overview of recommended cable tests	62
F.6	Main performance of a terminated cable	62
Annex G (informative) Recommended tests for performance evaluation of cables fixed into a divider and fan-out cables terminated with connectors.....		63
G.1	General.....	63
G.2	Connector types and design.....	63
G.3	Cable types.....	63
G.3.1	Cables	63
G.3.2	Fan-out cables.....	63
G.4	Termination of a cable into a divider and at fan-out cables.....	64
G.5	Overview of recommended cable tests	64
G.5.1	Recommended test for cable assembly.....	64
G.5.2	Recommended tests for cables	64
G.5.3	Recommended tests for fan-out cables	65
Annex H (informative) Recommended tests for performance evaluation of cables fixed into a protective housing and terminated with splices.....		66
H.1	General.....	66
H.2	Types of protective housings.....	66
H.3	Cable types.....	67
H.4	Termination of a cable in a protective housing	67
H.5	Overview of recommended cable tests	67
H.6	Main performance of a terminated cable	68
Annex I (informative) Recommended tests for performance evaluation of cables fixed into a protective housing and terminated with connectors		69
I.1	General.....	69
I.2	Types of protective housings.....	69
I.3	Cable types.....	69
I.4	Termination of a cable into a protective housing	69
I.5	Overview of recommended cable tests	70

I.6	Main performance of a terminated cable	70
Annex J (informative)	Recommended test parameters for change of temperature testing	71
J.1	Test methods and severities	71
J.2	Additional recommendations for the change of temperature test	72
Annex K (informative)	Cross-references of cable test methods	73
Bibliography	74
Figure 1	– Qualitative example of force during decreasing temperature of two polymer materials.....	13
Figure 2	– Cable sample for shrinkage testing according to Method F11	18
Figure 3	– Cable sample for fibre protrusion testing according to Method F17.....	19
Figure A.1	– Sheath shrinkage in mm of cable type 1 with different temperatures	31
Figure A.2	– Sheath shrinkage in mm of cable type 2 with different temperatures	32
Figure A.3	– Sheath shrinkage in mm of cable type 3 with different temperatures	33
Figure A.4	– Sheath shrinkage at different number of cycles	34
Figure A.5	– Change in attenuation during temperature cycling.....	35
Figure A.6	– Change in attenuation versus sheath shrinkage	36
Figure A.7	– Preparation of sample and measured lengths	38
Figure A.8	– Shrinkage of sheath and loose tube after different number of cycles	39
Figure A.9	– Preparation of sample and measured or calculated protrusion lengths	40
Figure A.10	– Protrusion length of cable type 1.....	41
Figure A.11	– Protrusion length of cable type 2.....	41
Figure A.12	– Protrusion length of cable type 3.....	42
Figure A.13	– Protrusion length of cable type 4.....	42
Figure A.14	– Change of fibre protrusion.....	44
Figure B.1	– Apparatus for holding cable samples	45
Figure B.2	– Temperature cycle with measurement points	46
Figure B.3	– Cable sheath length measurement results	47
Figure B.4	– Change in attenuation of orange cable samples at 1 310 nm	48
Figure B.5	– Change in attenuation of orange cable samples at 1 550 nm	48
Figure B.6	– Change in attenuation of orange cable samples at 1 625 nm	49
Figure B.7	– Change in attenuation of yellow cable samples at 1 310 nm.....	49
Figure B.8	– Change in attenuation of yellow cable samples at 1 550 nm.....	50
Figure B.9	– Change in attenuation of yellow cable samples at 1 625 nm.....	50
Figure D.1	– Cable terminated with connector plug	53
Figure D.2	– LC connector variants.....	53
Figure D.3	– Simplex cable terminated at LC simplex connector	54
Figure D.4	– Fibre movement in spring-loaded connectors.....	55
Figure D.5	– Simplex cable type	55
Figure D.6	– Duplex cable types	56
Figure D.7	– Test arrangement for method F12.....	58
Figure E.1	– Cable terminated with hardened connector	59
Figure F.1	– Cable fixed into a module and terminated with connectors	61

Figure G.1 – Cable fixed into a divider and fan-out cables terminated with connectors.....	63
Figure H.1 – Cable fixed into a protective housing and terminated with splices	66
Figure I.1 – Cable fixed into a protective housing and terminated with connectors	69
Figure J.1 – Change of temperature test configuration	72
Table 1 – Linear coefficients of thermal expansion of materials (informative)	12
Table 2 – Typical characteristics of indoor and outdoor cables.....	15
Table 3 – Overview of different termination cases	21
Table 4 – Temperature cycling severities for shrinkage testing for Methods F11A and F17	27
Table 5 – Recommended sheath shrinkage grades	27
Table 6 – Recommended change of fibre protrusion ΔL_1 grades	28
Table 7 – Recommended change of fibre protrusion ΔL_2 grades	28
Table A.1 – Overview of shrinkage results	34
Table A.2 – Overview of simplex results.....	35
Table A.3 – Details of loose tube cable types.....	37
Table A.4 – Details of unitube cable types	43
Table B.1 – Comparison of change in length with change in attenuation	51
Table C.1 – Shrinkage testing template.....	52
Table D.1 – Recommended tests for cables to be terminated with connectors.....	57
Table E.1 – Recommended tests for cables to be terminated with hardened connectors.....	60
Table F.1 – Recommended tests for cables fixed into module and terminated with connectors.....	62
Table G.1 – Recommended tests for cable assembly	64
Table G.2 – Recommended tests for cables fixed into dividers.....	64
Table G.3 – Recommended tests for fan-out cables	65
Table H.1 – Recommended tests for cables fixed at protective housing and terminated with splices	67
Table I.1 – Recommended tests for cables fixed into a protective housing and terminated with connectors	70
Table J.1 – Severities for change of temperature testing.....	71
Table K.1 – Cross reference table of mechanical test methods	73
Table K.2 – Cross reference table of environmental test methods	73

INTERNATIONAL ELECTROTECHNICAL COMMISSION

—————

**OPTICAL FIBRE CABLES –
SHRINKAGE EFFECTS ON CABLE AND CABLE
ELEMENT END TERMINATION – GUIDANCE**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a Technical Report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC TR 62959, which is a Technical Report, has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

The text of this technical report is based on the following documents:

Enquiry draft	Report on voting
86A/2032/DTR	86A/2058/RVDTR

Full information on the voting for the approval of this technical report can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

Cable shrinkage is sometimes used as a part of the performance criteria for optical fibre cables, including standard glass optical fibres for telecommunication application. However, there is only a partial correlation between shrinkage and other important cable parameters such as temperature performance and optical transmission characteristics, particularly during mechanical and environmental stress, since shrinkage strongly depends on the cable materials, the cable construction and the manufacturing processes.

The environmental performance of optical fibre cables is mainly determined using a suitable temperature cycling test while continuously measuring the change in attenuation during and after the test. Low shrinkage performance is not guaranteed by such a test method, so any cable shrinkage observed during and/or after the temperature cycle test can be used as an additional indicator for the characterisation of cables.

Cable shrinkage should be understood to include shrinkage of the entire cable, shrinkage of cable sub-assemblies such as units, and shrinkage of cable elements. It should also be understood that shrinkage of portions of the cable might be expressed as "growth" of other elements, such as fibres, strength members. Specific issues of cable shrinkage – buffer shrinkage, strength member growth, sheath shrinkage, etc. – should be carefully addressed when applying the principles of this document.

A combination of the passive component design (connectors, passive components, protective housings or cable management components) and cable shrinkage influences the cable/component performance. Excessive shrinkage at the cable/device interface can cause extra process steps and/or extra precautions to be taken at the interface and can cause degradation of the interface in service, for example the failure of strain relief effectiveness at a connector as the sheath shrinks back in use compromising the continuously optimal optical transmission parameters. Component manufacturers use a number of compensations for cable shrinkage in the design or assembly process of their components and will often select cables used in finished components for their low shrinkage performance. On the other hand, shrinkage can be compensated by installation technique.

To cover all relevant aspects of cables to be terminated, the recommended tests for performance evaluation of cables for different termination cases in addition to the optional tests for evaluation of shrinkage effects are included in this document.

This study into cable shrinkage was triggered by a CENELEC/TC86 BXA liaison letter sent to IEC/SC 86A in April 2016. The letter pointed out observed inconsistencies in indoor cable standards from a user point of view and asked for their concerns and recommendations to be addressed. The main subject was that jacket shrinkage should be a specified parameter for all indoor cables that are normally terminated by connectors, passive components or closures/enclosures.

A correspondence group in IEC/SC 86A/WG 3 was formed in 2016 to address issues about cable shrinkage. After discussion about relevant issues, cable shrinkage tests were performed, and the test results were collected and recorded. Annex A shows these test results and Clause 7 gives the conclusions of the cable shrinkage study. Generally, optical fibre cable types with a small outer diameter were involved in shrinkage testing. The results of different cable types from only a few cable manufactures were included, hence the number of cable types was limited and does not represent all cable types in the worldwide market. Subsequent work was done on recommendations for performance evaluation of cables to be terminated with connectors.

OPTICAL FIBRE CABLES – SHRINKAGE EFFECTS ON CABLE AND CABLE ELEMENT END TERMINATION – GUIDANCE

1 Scope

This document, which is a Technical Report, provides information on cable shrinkage characterisation of optical fibre cables that consist of standard glass optical fibres for telecommunication application. The characterisation is directed to the effects of cable shrinkage or cable element shrinkage on the termination of cables. Shrinkage can or cannot be a concern depending on the method of termination. Examples of different cable termination cases are included and described. Tests for the evaluation of cable shrinkage are recommended that can be used as indicators, and shrinkage classification by several grades are given.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60794-1-1, *Optical fibre cables – Part 1-1: Generic specification – General*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60794-1-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 shrinkage

irreversible contraction after extrusion of plastic materials caused by heating or over time at ambient temperature

Note 1 to entry: The irreversible contraction in the direction of the cable axis is usually called "cable shrinkage".

Note 2 to entry: This behaviour is also called "shrinkback".

3.2 thermal contraction

decrease in length of an element or assembly when subjected to a temperature increase or decrease

3.3 thermal expansion

increase in length of an element or assembly when subjected to a temperature increase or decrease