

Code of practice for

Fatigue design and assessment of steel structures

Committees responsible for this British Standard

The preparation of this British Standard was entrusted by the Welding Standards Policy Committee (WEE/-) to Technical Committee WEE/44, upon which the following bodies were represented:

AEA Technology
 Association of Consulting Engineers
 British Constructional Steelwork Association Ltd.
 British Railways Board
 Department of Transport
 Department of Transport (Transport Research Laboratory)
 ESDU International Ltd.
 Electricity Association
 Federation of Manufacturers of Construction Equipment and Cranes
 Institution of Civil Engineers
 Institution of Structural Engineers
 Ministry of Defence
 Process Plant Association
 Railway Industry Association of Great Britain
 Society of British Aerospace Companies Limited
 United Kingdom Offshore Operators Association
 Welding Institute

This British Standard, having been prepared under the direction of the Welding Standards Policy Committee, was published under the authority of the Standards Board and comes into effect on 15 April 1993

© BSI 03-1999

The following BSI references relate to the work on this standard:
 Committee reference WEE/44
 Draft for comment 87/77328 DC

ISBN 0 580 21281 5

Amendments issued since publication

Amd. No.	Date	Comments
8337	February 1995	Indicated by a sideline in the margin

Contents

	Page
Committees responsible	Inside front cover
Foreword	iv
<hr/>	
Section 1. General	
1.1 Scope	1
1.2 References	1
1.3 Definitions	1
1.4 Symbols and units	3
1.5 Assessment	3
1.6 Design life	3
1.7 Fatigue loading	3
1.8 Basis of fatigue analysis	4
1.9 Factors on fatigue life	4
1.10 Features influencing fatigue behaviour	5
1.11 Fracture mechanics	5
<hr/>	
Section 2. Classification of details	
2.1 General	6
2.2 Classification of details	6
2.3 Unclassified details	24
2.4 Workmanship and inspection	24
2.5 Welded steel decks	25
<hr/>	
Section 3. Stress calculations	
3.1 General	27
3.2 Stress range in parent material	27
3.3 Stress range for welds	27
3.4 Effective stress range for details in unwelded members in which the whole or part of the stress is compressive	27
3.5 Calculation of stresses	27
3.6 Geometrical stress concentrations	28
3.7 Stresses in welds attaching shear connectors	29
3.8 Axial stresses in bolts	30
3.9 Derivation of stress spectra	30
<hr/>	
Section 4. Allowable fatigue stresses	
4.1 Tensile stress limitations	31
4.2 <i>S-N</i> curves	31
4.3 Modifications to basic <i>S-N</i> curves	31
4.4 Treatment of low stress cycles	33
4.5 Treatment of high stress cycles	34
4.6 Joints subjected to single stress range	34
4.7 Joints subjected to a stress spectrum	34
<hr/>	
Annex A (normative) Fatigue design philosophy	46
Annex B (normative) Explanatory notes on detail classification	47
Annex C (normative) Guidance on the calculation of stress concentration factors	51
Annex D (normative) Guidance on the use of fracture mechanics	61
Annex E (normative) Fatigue testing and the use of test data to define design stresses	69
Annex F (normative) Cycle counting by the reservoir method	70
Annex G (informative) Background notes on sources of data	71

	Page
Annex H (informative) Bibliography	80
Figure 1 — Weld quality category determined by adjacent detail	35
Figure 2 — Reference stress in parent metal	36
Figure 3 — Reference stress in weld throat	36
Figure 4 — Typical example of stress concentrations due to geometrical discontinuity	37
Figure 5 — Typical example of stress concentration caused by a geometrical hard spot	38
Figure 6 — Stress concentration factors	39
Figure 7 — Example of hot spot stresses in a nodal joint	40
Figure 8 — Summary of mean-line S_r - N curves	41
Figure 9 — Summary of standard basic design S_r - N curves	42
Figure 10 — S_r /UTS- N curves for bolts with cut or, ground or rolled threads under axial loading (class X)	43
Figure 11 — Toe grinding to improve fatigue strength	44
Figure 12 — Grinding of weld at tubular nodal joint	45
Figure 13 — Typical S_r - N relationship	45
Figure B.1 — Edge distance	52
Figure B.2 — Failure modes at weld ends	52
Figure B.3 — Failure modes in cruciform and T-joints	53
Figure B.4 — Failure modes in transverse butt welds	53
Figure B.5 — T-junction of two flange plates	53
Figure B.6 — Cruciform junction between flange plates	54
Figure B.7 — Alternative method of joining two flange plates	54
Figure B.8 — Local grinding adjacent to cope hole in type 7.1 joint	55
Figure B.9 — Use of continuity plating to reduce stress concentrations in type 8.1 and 8.2 joints	55
Figure B.10 — Example of type 8.3 or 8.4 joint	56
Figure B.11 — Single fillet corner weld in bending	56
Figure B.12 — Example of a third member slotted through a main member	57
Figure C.1 — Types of misalignment and distortion	61
Figure D.1 — Flaw dimensions	63
Figure D.2 — Transverse load-carrying cruciform joint	64
Figure F.1 — Example of cycle counting by reservoir method	70
Figure G.1 — Comparison of proposed S - N curves for bolts in axial loading with curves from ESDU data sheets	79
Table 1 — Classification of details: plain material free from welding	7
Table 2 — Classification of details: bolted or rivetted, spliced or lapped connections	8
Table 3 — Classification of details: fasteners and shear connectors	9
Table 4 — Classification of details: continuous welded attachments essentially parallel to the direction of applied stress	10
Table 5 — Classification of details: welded attachments on the surface or edge of a stressed member	12
Table 6 — Classification of details: full penetration butt welds between co-planar plates	13
Table 7 — Classification of details: transverse butt welds in sections and tubes	15

	Page
Table 8 — Classification of details: load carrying fillet and T-butt joints between plates in different planes	17
Table 9 — Classification of details: slotted connections and penetration through stressed members	20
Table 10 — Classification of details: circular tubular members	21
Table 11 — Classification of details: seam welds	22
Table 12 — Classification of details: branch connections	23
Table 13 — Upper limits of flaw area of planar flaws and slag inclusions in transverse butt welds	26
Table 14 — Details of basic $S-N$ curves	32
Table 15 — Nominal probability factors	33
Table D.1 — Values of M_1 , M_2 and M_3	66
Table D.2 — Values of g and f_ϕ	67
Table E.1 — Fatigue test factor F	70
Table G.1 — Sources of the content	72
Table G.2 — Experimentally determined fatigue strengths of various types of threaded connection expressed in terms of stress range/UTS	77
List of references	Inside back cover

Foreword

This British Standard has been prepared under the direction of the Welding Standards Policy Committee.

It has been produced with the objective of covering the general aspects of fatigue design of fabricated steel elements within the subject area regardless of the type of structure in which they are situated. It is anticipated that application standards for particular types of structure will in due course be modified to omit their own fatigue design rules and to cross refer to this code of practice, thereby achieving a co-ordinated approach to the subject. Such application standards will, however, still include fatigue loading and safety requirements for the structures to which they relate.

This code is based directly upon the recommendations of existing codes and other reference documents, such as the Department of Energy Publication *Offshore installations: Guidance on design, construction and certification*. At this stage no attempt has been made to update existing recommendations except in cases where they were found to be in need of clarification. Background notes on the sources of the data given in this code are provided in Annex G.

As a code of practice, this British Standard takes the form of guidance and recommendations. It should not be quoted as if it were a specification and particular care should be taken to ensure that claims of compliance are not misleading.

It has been assumed in the drafting of this British Standard that the execution of its provisions is entrusted to appropriately qualified and experienced people.

NOTE The numbers in square brackets used throughout the text of this British Standard relate to the bibliographic references given in Annex H.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i to iv, pages 1 to 80, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

Section 1. General

1.1 Scope

This British Standard gives recommendations for methods for the fatigue design and assessment of parts of steel structures which are subject to repeated fluctuations of stress. It is concerned with wrought structural steel with a specified minimum yield strength of up to 700 N/mm^2 operating in the sub-creep regime.

This British Standard is applicable to the following:

- a) parent material remote from joints;
- b) welded joints (in air or sea water) in such material¹⁾;
- c) bolted or rivetted joints in such material;
- d) shear connectors between concrete slabs and steel girders acting compositely in flexure.

Guidance on general fatigue design philosophy is given in Annex A, which also contains a brief description of the method of using this document.

The relevant application standard or other specification for the particular structure under consideration should specify the following:

- 1) the loading to be assumed for design purposes, including its magnitude and frequency;
- 2) the required life of the structure;
- 3) the environmental conditions;
- 4) the required nominal probability of failure (see 4.2).

This British Standard takes no account of the possible onset of unstable fracture from a fatigue crack. This possibility should be considered and guarded against by appropriate material selection.

This British Standard does not apply to the following:

- orthotropic decks;
- wire ropes;
- bonded connections;
- steel reinforcement in concrete;
- out of plane joints between hot rolled rectangular or square hollow sections;
- pressure vessels;
- castings;
- peening.

1.2 References

1.2.1 Normative references

This British Standard incorporates, by reference, provisions from specific editions of other publications. These normative references are cited at the appropriate points in the text and the publications are listed on the inside back cover. Subsequent amendments to, or revisions of, any of these publications apply to this British Standard only when incorporated in it by updating or revision.

1.2.2 Informative references

This British Standard refers to other publications that provide information or guidance. Editions of these publications current at the time of issue of this standard are listed on the inside back cover, but reference should be made to the latest editions.

1.3 Definitions

For the purposes of this British Standard the following definitions apply.

1.3.1 fatigue

the damage of a structural part by the initiation and gradual propagation of a crack or cracks caused by repeated applications of stress

1.3.2 stress cycle

a pattern of variation of stress at a point defined by the cycle counting method and consisting of a change in stress between defined minimum (trough) and maximum (peak) values and back again

NOTE 1 Also known as cycle of stress.

NOTE 2 One loading event may produce one or more stress cycles at any particular point.

1.3.3 stress range S_r

the algebraic difference between the two extremes (reversals) of a stress cycle

NOTE 1 Also known as range of stress.

NOTE 2 See 3.2 and 3.3 for parent metal and weld metal respectively.

1.3.4 initial non-propagating stress range S_0

the constant amplitude stress range below which (in the absence of any previous loading) a crack is assumed not to propagate

NOTE Its magnitude depends on the joint class and, for joints in air or adequately protected against corrosion, it is assumed to be the stress corresponding to a life of 10^7 cycles on the design $S-N$ curve. For unprotected joints in a corrosive environment it should be assumed that $S_0 = 0$.

¹⁾ For welded joints fatigue strength is same for all steels.